



Quartz Sand F 36

Filler for the Remmers KSE module system

| Colour | Availability | | |
|--------------------------|---------------------|-----------|-----------|
| | Quantity per pallet | 80 | 36 |
| | Packaging unit | 4 kg | 25 kg |
| | Type of container | Paper bag | Paper bag |
| | Container code | 04 | 25 |
| | Art. no. | | |
| beige (intrinsic colour) | 0570 | ■ | ■ |

Application rate Dependent on the application

Range of use



- Producing KSE-bound quartz sand grouts
- Backfilling compounds
- Battering mortar

Property profile ■ Furnace-dried

Characteristic data of the product

| | |
|------------------------------|--------------------------------|
| Density (20 °C) | approx. 2.65 g/cm ³ |
| Theoretical specific surface | approx. 149 cm ² /g |
| Composition | approx. 99% quartz by mass |
| Mean grain size | approx. 0.16 mm |

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products

- [KSE 500 STE \(0713\)](#)
- [KSE Filler A \(0571\)](#)
- [KSE Filler B \(0572\)](#)


Directions Tips on use and guide formulations can be found in the technical guidelines for the KSE module system.

Notes Deviations from applicable regulations must be agreed separately.
The relevant test certificates must be observed when planning and carrying out work.



Storage / Shelf life

If stored in unopened sacks in a cool, dry place, the product will keep for at least 12 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.