





Apply the jointing in two layers if possible, press in the jointing mortar and level flush but do not "iron".  
After application, work with a profiling tool (e.g. tubing).

Tips on use

Only mix as much mortar as can be used within approx. 2 hours.  
Once it has hardened, mortar must not be made workable again by adding either water or more wet mortar.  
Protect wet mortar surfaces against frost, rain and drying out too quickly for at least 4 days.

Notes

The colour that is obtained after drying and hardening depends on the ambient conditions and the processing method. For instance, a freshly smoothed surface will be lighter than one that is smoothed later or roughened. Different grain sizes of the same product may lead to slight differences in colour. Substrates soaked from the back may cause discolouration.  
The mixing water must be of drinking water quality.  
May contain traces of pyrite (iron sulphide).  
Do not use on gypsum-based substrates.  
Low chromate content in accordance with Directive 2003/53/EC.  
The characteristic data of the product were calculated under laboratory conditions at 20°C and 65% relative humidity.


Tools / Cleaning



Mixing tool, trowel, jointing iron  
Clean tools with water while the material is still fresh.

- Remmers tools
- > Mischgefäß (4030)
  - > Collomix® Stirrer KR (4292)

Storage / Shelf life



If stored in an unopened container and in a dry place, the product will keep for approx. 12 months.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.