Technical Data Sheet Product number 0607







Façade Impregnation [basic]

Clear, solvent-based hydrophobic impregnation, silane/siloxane-based

	Availability				
	Quantity per pallet	84	50	24	
	Size / Quantity	5 l	10 l	30 l	
	Type of container	Tin canister	Tin canister	Tin canister	
	Container code	05	10	30	
	Art. no.				
	0607				
Application rate	Brickwork, fine-pored: min. 1.0 l/m² Brickwork, large-pored: min. 1.2 l/m² Sand/lime brick, smooth: min. 0.6 l/m²				
400-1800 ml					
111	Sand/lime brick, shlooti, init, o.o (/ m Sand/lime brick, natural split, bossed: min. 0.9 l/m ²				
1m ²	Render: min. 0.6 l/m²				
	Porous concrete: min. 1.2 l/m ²				
	Fibre cement: min. 0.4 l/m²				
	Modular concrete blocks: min. 1.5 l/m² Natural stone, fine-pored: min. 0.8 l/m²				
	Natural stone, large-pored: min. 1.8 l/m²				
	Apply to a large enough trial surface (1-2 m ²) to determine the precise amount of impregnation agent required.				
Range of use	Protection of facades against drivi	ng rain			
	 Reduces susceptibility to dirt and green discolouration 				
•	Subsequent treatment/renewal of hydrophobic surfaces				
	Porous, mineral building materials such as brick masonry work, sandstone/sand-lime brick, mineral renders and				
	aerated concrete Not suitable for materials that are sensitive to solvents, such as polystyrene or bitumen.				
	Not suitable for materials that are	sensitive to solvents, suc	in as polystyrene or bitu	men.	
Property profile	Improves resistance to frost and d	le-icing salts			
	Repels water				
	 Enables water vapour diffusion UV-resistant 				
	 OV-resistant Alkali-resistant 				
	Reduces energy loss				
Characteristic data of the product	Carrier material Dearomatised hydrocarbons				
	Density (20 °C)	Approx. 0.8 g/cm ³			
	Runout time s in DIN 2 cup	Approx. 44			
	Active ingredient	Silane/siloxane			
	Active ingredient content, % by mass	ent content, % by Approx. 6			
	Flash point °C	> 40 °C			
	Appearance/colour	Clear, liquid			
	The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.				
Possible system products	> BFA* (0673)				
	 Remmers cleaning products 				
	 Remmers jointing mortars 				
	*Use biocidal products carefully.				
	Always read the label and product inform	nation before use.			

Façade Impregnation

	The substrate must be clean, dust-free and dry.	
	Substrate preparation Any construction defects such as cracks, cracked joints, defective connections, rising damp and hygroscopic moisture must be remedied in advance. Perform any necessary cleaning gently, e.g. by spraying with cold or warm water or by steam-cleaning; use rotec soft whirl jet technology or Remmers cleaning products (e.g. Traffic Film Remover (0671), Clean FP (0666), Clean AC (0672), Combi WR (0675)) on tough stains.	
Directions	During application of Funcosil SNL and while it is drying, solvent vapours may enter the building through windows and doors, in particular at low temperatures and on days with no wind. It is therefore important that windows and doors remain closed during application. Ventilate rooms thoroughly once the hydrophobic agent has dried. On surfaces where spray application is not possible, apply using a well-saturated brush.	
Tips on use	Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product. Protect freshly treated surfaces from driving rain, wind, sunlight and condensation. Remove any excess impregnation agent within 1 hour using V 101 thinner. During application and drying of solvent-based impregnation agents, we recommend keeping windows and doors closed.	
Notes	Deviations from applicable regulations must be agreed separately. The relevant test certificates must be observed when planning and carrying out work. Water must not be allowed to penetrate behind the hydrophobized zone. The level of absorption is crucial for the impregnation agent to work at its best. This depends on the respective pore volume and moisture content of the building material. Carry out a quantitative analysis of aggressive salts if there are any salts present that could damage building materials. High concentrations of harmful salts can cause major structural damage that impregnation cannot prevent. Testing effectiveness: The water absorption of mineral building materials can be determined using the Funcosil Test Tube developed by Professor Karsten (Funcosil Facade Testing Kit, article no. 4954). Testing can only be carried out at the earliest 6 weeks after application. A test of effectiveness needs to be carried out on carbonaceous natural stone. Always set up a trial area/trial areas first.	
Tools / Cleaning	Solvent-resistant, low-pressure conveying and spraying equipment, liquid pump, paintbrush and flat brush Tools must be clean and dry.	
	 After use and before prolonged interruptions of work clean tools with Thinner V 101. Remmers tools Funcosil Test-Set (4954) Diagnosekoffer für Mauerwerkssanierung (4953) Gloria CleanMaster PERFORMANCE PF 50 (4666) 	
Storage / Shelf life	If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months. Use the contents of open containers as quickly as possible.	
Safety data / Regulations	For further information on the safety aspects of transporting, storing and handling the product and on disposal ar environmental matters, please see the current Safety Data Sheet.	
Personal protective equipment	Respiratory protection with at least an A/P2 combination filter must be worn during spraying, together with safety goggles. Wear suitable protective gloves and clothing.	
Disposal	Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.	

Technical Data Sheet Product number 0607



Façade Impregnation



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.