Technical Data Sheet Product number 0662







## Clean Galena neutral

Cleaner for emission-free cleaning of mineral surfaces

Type/Name	Availability		
	Quantity per pallet	288	12
	Size / Quantity	1 kg	25 kg
	Type of container	Plastic bucket	Plastic bucket
	Container code	01	25
	Art. no.		
Clean Galena neutral	0662		
Clean Galena max	0661		
Special formulation			
Clean Galena individual	0664		
By special agreement only, min. 2 weeks	s lead time, minimum order quantity approx. 1,000 kg		
pplication rate		n rate on a sufficiently large, represent	
2-3 kg	Standard wet film thickness 2.5 m Determine the precise application	n	
2-3 kg Total ↓ ↓ ↓	Standard wet film thickness 2.5 m Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime	n rate on a sufficiently large, represent e application rate is reduced accordin estone	
$\begin{array}{c} 2 \cdot 3 \text{ kg} \\ \hline \text{Total} \\ \downarrow \\ 1 \text{ m}^2 \end{array}$	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th	n rate on a sufficiently large, represent e application rate is reduced accordin estone	
$\begin{array}{c} 2 \cdot 3 \text{ kg} \\ \hline \text{Total} \\ \downarrow \\ 1 \text{ m}^2 \end{array}$	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead	
$\begin{array}{c} 2 \cdot 3 \text{ kg} \\ \hline \text{Total} \\ \downarrow \\ 1 \text{ m}^2 \end{array}$	Standard wet film thickness 2.5 m Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead	
$\begin{array}{c} 2 \cdot 3 \text{ kg} \\ \hline \text{Total} \\ \downarrow \\ 1 \text{ m}^2 \end{array}$	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead or copper compounds	
ange of use	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron For use by professionals Low quantity of active cleaning su Gentle cleaning	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead or copper compounds	
ange of use	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron of For use by professionals	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead or copper compounds bstances	
ange of use	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron For use by professionals Low quantity of active cleaning su Gentle cleaning Emission-free Dries to form an easily removable Binds impurities in the surface	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead or copper compounds bstances	
ange of use	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron For use by professionals Low quantity of active cleaning su Gentle cleaning Emission-free Dries to form an easily removable	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead or copper compounds bstances	
ange of use	Standard wet film thickness 2.5 mi Determine the precise application When mixed with Clean Galena, th Mineral surfaces, in particular lime Reduction of heavy metals, in part Reduction of encrusted dirt Removal of stains caused by iron For use by professionals Low quantity of active cleaning su Gentle cleaning Emission-free Dries to form an easily removable Binds impurities in the surface	n rate on a sufficiently large, represent e application rate is reduced accordin estone icular lead or copper compounds bstances	

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.



1



Possible system products	<ul> <li>Clean Galena max (0661)</li> <li>LEAD Box (4969)</li> </ul>		
Preparation	Substrate requirements Stable and free of dust.		
	<ul> <li>Substrate preparation         Use a suitable tool to coarsely clean off the substrate.         Set up a trial area to determine the cleaning effect.         Take appropriate measures to protect adjacent building elements and materials that should not come into contact         with the product.         Thoroughly pre-wet the substrate.</li> </ul>		
Directions	For professional users only!		
= +30 °C	Conditions for use Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.		
	Stir well. If necessary, mix the material with Clean Galena max to modify the cleaning effect and drying behaviour. We recommend setting up at least 3 trial surfaces: undiluted Clean Galena neutral, Clean Galena neutral with Clean Galena max 1:1, and undiluted Clean Galena max. Document the mixing ratio.		
	Apply to the entire surface area of the substrate using a suitable tool. Fill undercut areas and contours thoroughly with the material. Once completely dry (usually 1 to 3 days after application), remove the film by carefully detaching using a spatula. After removing the skin, clean the treated surfaces with a sponge and fresh water, as well as hot steam if necessary, starting from the lowest point. Further cleaning procedures might be necessary, depending on the degree of contamination and the substrate. If needed, repeat the application.		
Tips on use	Please contact Remmers Technical Service (phone +49 5432 83900) before applying with machine processing. The drying time depends on the substrate, the coating thicknesses and the climate conditions. The substrate must be free from biological contamination such as moss, algae and mould.		
Notes	Always set up a sufficiently large, representative trial area or areas! Deviations from applicable regulations must be agreed separately. The relevant test certificates must be observed when planning and carrying out work.		
Tools / Cleaning	Paintbrush, scraper, smoothing trowel, airless spraying equipment, peristaltic pump Clean tools immediately after use with water and detergent.		

Clean Galena neutral

for at least 12 months.





Storage / Shelf life

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Any material that is contaminated after application must be disposed of in accordance with the applicable regulations.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.