



Primer Hydro HF

- Hydro Deep Primer -

Aqueous deep primer with strengthening and hydrophobising properties

Availability			
Quantity per pallet	90	24	
Size / Quantity	5 l	30 l	
Type of container	Plastic canister	Plastic canister	
Container code	05	30	
Art. no.	0725	■	■

Application rate

Approx. 0.1 - 0.2 l/m² depending on the substrate

Apply to a large enough trial area to determine the precise amount required.



Range of use

- Primer for sanding, mineral substrates such as P II and P III
- Weathered old coatings capable of supporting a load



Property profile

- Strengthens
- Equalises absorption capacity
- Aqueous



Characteristic data of the product

Carrier material	Water
Solids content	Approx. 8%
Density (20 °C)	Approx. 1.0 g/cm ³
Flash point °C	Non-combustible – water-dilutable
pH value	8.5
Appearance	Milky white

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products


- Color LA (6400)
- Color LA Fill (0560)
- Color PA (6500)
- Color SF [basic] (6415)
- WP Flow (0431)

Preparation

- Substrate requirements
Clean, dry and free of dust and cracks (apart from hairline cracks).
Free of salts known to be damaging to building materials.

Directions

- Conditions for use
Temperature of the material, air and substrate: from min. +5 °C to max. +25 °C.
- Apply with a brush, roller or by spraying.
Shake well before use.
If needed, repeat the application.





Tips on use

Adjacent building elements and materials that are not intended to come into contact with the product should be protected using suitable measures.
Structural defects such as cracks, cracked joints, defective connections and rising damp must be remedied first.
Do not let excess material build up on the surface.
Can be diluted with water depending on the absorbency of the substrate.
Glossy layers must be avoided.

■ Drying

Can be recoated after 12 hours at +20 °C and 65% relative humidity.
As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Notes

The relevant test certificates must be observed when planning and carrying out work.
The current technical regulations must be observed.
Deviations from applicable regulations must be agreed separately.
Always set up a trial area/trial areas first.

Tools / Cleaning




Paintbrush, ceiling brush, flat brush, pressure sprayer

Clean tools immediately after use with water.

Remmers tools

- Gloria Drucksprüher Pro 100 (4668)
- Gloria CleanMaster PERFORMANCE PF 50 (4666)
- Gloria CleanMaster EXTREME EX 100 (4665)
- Flächenstreicher (4540)
- Farbrolle FC (4913)
- Rollerbügel (4449)
- Heizkörperpinsel (4541)

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/h): max. 30 g/l (2010).
This product contains < 1 g/l VOC.

VOC	
Kat.	A/h
2010:	30g/l
max.:	< 1 g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.