



Epoxy Quick 100

Fast-reacting primer and mortar resin

Availability				
Quantity per pallet	168	120		
Size / Quantity	1 kg	2,5 kg	10 kg	25 kg
Type of container	Multi-chamber bag	Multi-chamber bag	Tin bucket	Tin bucket
Container code	01	03	11	26
Art. no.				
0899			■	■
6097	■	■		

Application rate See application examples

Range of use

- Primer, bonding layer, levelling layer
- Producing compression-resistant mortars, flow coatings
- Base layer for blinded covers

Property profile

- Fast curing / can be coated after a short time
- Full hardening from +3 °C
- Can be subjected to mechanical loads
- Can be subjected to chemical loads
- Free from plasticisers and nonylphenols
- Physiologically harmless once fully cured
- Suitable for use as primer without broadcasting underneath Remmers PU and EU coatings

Characteristic data of the product

- **On delivery**

	Component A	Component B	Mixture
Density (20 °C)	1.16 g/cm ³	0.97 g/cm ³	1.08 g/cm ³
Viscosity (25 °C)	950 mPa s	800 mPa s	800 mPa s
- **Once fully cured**

Flexural tensile strength	approx. 20 N/mm ² *
Compressive strength	approx. 65 N/mm ² *

* Epoxy resin mortar 1:10 with standard sand
The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- > [Beständigkeit \(Chemikalien\)](#)
- > [Nachhaltigkeitsdatenblatt](#)

Preparation

- **Substrate requirements**
The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion. The tensile strength of the surface of the substrate must be at least 1.5 N/mm² on average (smallest individual value of at least 1.0 N/mm²), and the compressive strength must be at least 25 N/mm². Substrates must have reached their moisture balance and must also be protected against moisture penetration from the reverse side, including during use.

Concrete	max. 4 m% moisture
Cement screed	max. 4 m% moisture
Anhydrite screed	max. 0.3 m% moisture




Magnesite screed	2-4 m% moisture
------------------	-----------------

In the case of anhydrite and magnesite screeds, moisture cannot be permitted to penetrate from building elements or the ground.
As a general principle, systems which permit the diffusion of water vapour are recommended for use with anhydrite and magnesite screeds.

■ **Substrate preparation**

Prepare the substrate by suitable means, e.g. steel ball jetting or diamond grinding, so that it meets the requirements specified above.
Broken-out or missing areas in the substrate should be filled flush with the surface using Remmers RM systems (RM = Repair Mortar) or Remmers EP mortars.

Production of the mixture



■ **Multi-chamber bag**

Open the outer packaging along the perforation and remove the transparent multi-chamber bag. Remove the dividing strip on the bag. Then mix the two components together by kneading the contents of the bag intensively (approx. 60 seconds).

■ **Combi-container**

Add the entire quantity of the hardener (component B) to the base compound (component A).
Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).
Pour the mixture into a separate container and mix again thoroughly.
Mix for at least 3 minutes.
Insufficient mixing is indicated by streaks forming.

Mixing ratio (A : B)	75 : 25 parts by weight
-----------------------------	-------------------------

In the case of filled systems, slowly stir the corresponding quantity of filler into the reaction resin mixture and mix thoroughly.
As soon as the mixture is ready to use, apply all of it to the prepared surface and spread it using a suitable tool.

Directions



For professional users only!

■ **Conditions for use**

Temperature of the material, air and substrate: from min. +3 °C to max. +25 °C
During the curing process, the applied material should be protected from moisture which could impair the surface and impair the adhesion.
Relative humidity should not exceed 80%.
The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.

■ **Working time (+20 °C)**

approx. 15 minutes

■ **Waiting time (+20 °C)**

Waiting time between coats min. 2 hours and max. 6 hours.
If waiting times are longer due to site conditions, the surface of the previous coat must be broadcast in a specific manner with fire-dried quartz sand (e.g. grain size 0.3-0.8 mm) while fresh or sanded back until stress-whitening begins to occur before proceeding to the next step.

■ **Drying time (+20 °C)**

Foot traffic after 3 hours, mechanical loading after 1 day, full loading capacity after 3 days.

As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Application examples

■ **Priming**

Apply the mixed resin generously to the surface. Distribute with a suitable tool, e.g. rubber blade, and work into the substrate with an epoxy roller so that pores in the surface of the substrate are completely filled.
It may be necessary to apply several layers.

Application rate	approx. 0.30 - 0.50 kg/m ² binder (depending on the substrate)
------------------	---

■ **Levelling layer/scratch coat**

Apply the filled material (up to 1 : 1 parts by weight) to the primed surface and distribute with a suitable trowel. If necessary, roll over with a spiked roller.

Application rate	Per mm thickness of base layer: approx. 0.85 kg/m ² binder and 0.85 kg/m ² Selectmix 01/03
------------------	--



■ **Synthetic resin mortar**

Spread and smooth out the filled material (up to 1 : 10 parts by weight) with a smoothing trowel.

Application rate	Per mm layer thickness: approx. 0.2 kg/m ² binder and 2.0 kg/m ² Selectmix 25
------------------	---

■ **Base layer for blinded coatings**

Apply the filled material (up to 1 : 1 parts by weight) to the primed surface and distribute with a suitable toothed trowel or toothed rubber blade. If necessary, roll over with a spiked roller.

Liberally broadcast fire-dried quartz sand over the base layer while it is still fresh.

Remove any loose, excess material after hardening.

Application rate	Per mm thickness of base layer: approx. 0.85 kg/m ² binder and 0.85 kg/m ² Selectmix 01/03
------------------	--

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C). Slight deviations from these values may arise if the product is worked with on site.

Primers must always be applied so that all pores are filled; it may therefore be necessary to increase the application rate or to apply a second coat.

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.

Abrasive mechanical loads leave traces of wear.

Epoxy resins are generally not colourfast when exposed to UV light or weather.

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

Tools / Cleaning



Smoothing trowel, toothed trowel, notched spreader, rubber scraper, epoxy roller, spiked roller, mixer, positive mixer if necessary

More detailed information can be found in the Remmers Tool Programme.


Clean tools, equipment and splashed material immediately while fresh with V 101.

Take suitable protective and waste disposal measures when cleaning.

Remmers tools

- > [Collomix AR 170 \(4247\)](#)
- > [Patentdispenser \(4747\)](#)

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months.

Safety data / Regulations

For professional users only!

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet and the brochure entitled "Epoxy Resins in the Construction Industry and the Environment", issued by Deutsche Bauchemie e.V. (3rd edition 2022).

Personal protective equipment

This information can be obtained from the current Safety Data Sheets and/or the relevant professional associations.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/j): max. 500 g/l (2010).
This product contains < 500 g/l VOC.

Declaration of performance

> [Declaration of performance](#)



Declaration of conformity



Remmers GmbH

Bernhard-Remmers-Str. 13, D – 49624 Lönigen

11

GBIII 026_4

EN 13813:2002

0899

Synthetic resin screed for use internally in buildings

Reaction to fire:	E _{fl}
Release of corrosive substances:	SR
Wear resistance:	≤ AR 1
Bond strength:	≥ B 1.5
Impact resistance:	≥ IR 4

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.