



## Desalting Compress

Dry mortar used to reduce salts near the surface

Colour	Availability	
	Quantity per pallet	42
	<b>Size / Quantity</b>	<b>20 kg</b>
	Type of container	PE bag
	Container code	20
	<b>Art. no.</b>	
grey-beige	1070	■

### Application rate

Approx. 14 kg/m<sup>2</sup>/cm layer thickness, depending on the conditions of the substrate  
Apply to a large enough trial area to determine the precise amount required.



### Range of use

- Non-destructive reduction of salt content in a poultice procedure in accordance with WTA Code of Practice 3-13-01



### Property profile

- Highly effective poultice material made from a combination of active mineral constituents and cellulose
- Free of cement and lime
- Optimised transfer of moisture and salt through lightweight, capillary-active aggregates
- Does not leave any residue and is easy to remove
- "Drying compress" mechanism

### Characteristic data of the product

Bulk density	Approx. 1.4 kg/dm <sup>3</sup>
Water requirement	Approx. 6.6 - 7.3 l/20 kg


The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

### Preparation

- Substrate requirements  
Clean, dust-free and capable of supporting a load.
- Substrate preparation  
Pre-wet the substrate using deionised water so that it is matt damp.


### Production of the mixture

- Mixing  
Pour distilled or deionised water into a clean container before adding dry mortar.  
Mix thoroughly for approximately 3 minutes until the proper consistency for working has been achieved.



### Directions

- Conditions for use  
Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.  
Low temperatures increase, while high temperatures decrease the working and setting time.
- Apply the product in a layer measuring 10-20 mm thick.  
Following a sufficient period in which the product is left to stand, carefully remove the compress. If necessary, repeat the process and carry out testing in parallel.




### Tips on use

Analyse the salt content before and after application (BRIFA).  
Monitor the drying progress on a continual basis and, if necessary, protect from drying out too quickly.



---

	Compresses that have dried out should be removed without delay. Hairline/shrinkage cracks are safe and are not cause for complaint as they do not impair the properties of the mortar.
Notes	Wear a dust mask (see Safety Data Sheet). Do not use on gypsum-based substrates. Always set up a trial area/trial areas first. Further information can be found in the WTA Code of Practice 3-13-01/D.
Tools / Cleaning	Mixer, smoothing trowel, levelling trowel, aluminium float  Clean tools with water while the material is still fresh.  Remmers tools <ul style="list-style-type: none"><li>&gt; <a href="#">Mischgefäß (4030)</a></li><li>&gt; <a href="#">Smoothing Trowel (4004)</a></li><li>&gt; <a href="#">Glättkelle (4117)</a></li><li>&gt; <a href="#">Smoothing Trowel Duo (4118)</a></li></ul>
Storage / Shelf life	If stored in an unopened container and in a dry place, the product will keep for approx. 12 months.
Safety data / Regulations	For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.
Disposal	Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.