



Epoxy GL 100

Transparent priming and mortar resin in systems requiring authorisation



Availability			
Quantity per pallet			
Size / Quantity	10 kg	25 kg	
Type of container	Tin bucket	Tin bucket	
Container code	11	26	
Art. no.			
1427	■	■	

Application rate See application examples

Range of use

- Primer, bonding layer, levelling layer
- Primer in the system SL Floor WHG (AbZ Z-59.12-302)
- Primer in the system SL Floor WHG AS (AbZ Z-59.12-303)

Property profile

- Can be subjected to mechanical loads
- Can be subjected to chemical loads
- Good penetration characteristics
- Contains no plasticisers, nonylphenols or alkylphenols
- Physiologically harmless once fully cured
- Suitable for use as primer without broadcasting underneath Remmers PU and EU coatings

Characteristic data of the product

	Component A	Component B	Mixture
Density (20 °C)	1.12 g/cm ³	1.03 g/cm ³	1.10 g/cm ³
Viscosity (25 °C)	870 mPa s	200 mPa s	600 mPa s

■ Once fully cured

Flexural tensile strength	approx. 10 N/mm ² *
Compressive strength	approx. 40 N/mm ² *

* Epoxy resin mortar 1 : 10 with standard sand

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- Brandprüfung (Klassifizierung) SL Floor Flex
- Übereinstimmungszertifikat SL Floor WHG
- Übereinstimmungszertifikat SL Floor WHG AS
- Allgemeine bauaufsichtliche Zulassung SL Floor WHG
- Allgemeine bauaufsichtliche Zulassung SL Floor WHG AS
- Beständigkeit (Chemikalien)
- Nachhaltigkeitsdatenblatt

Possible system products

- Epoxy OS Color (6980)
- PUR Uni Color (6800)
- Epoxy WHG Color (1428)
- Epoxy WHG Color AS (1431)

Preparation

- Substrate requirements
The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.



The tensile strength of the surface of the substrate must be at least 1.5 N/mm² on average (smallest individual value of at least 1.0 N/mm²), and the compressive strength must be at least 25 N/mm². Substrates must have reached their moisture balance and must also be protected against moisture penetration from the reverse side, including during use.

Concrete	max. 4 m% moisture
Cement screed	max. 4 m% moisture
Anhydrite screed	max. 0.3 m% moisture
Magnesite screed	2-4 m% moisture


In the case of anhydrite and magnesite screeds, moisture cannot be permitted to penetrate from building elements or the ground.

As a general principle, systems which permit the diffusion of water vapour are recommended for use with anhydrite and magnesite screeds.

For collecting basins in facilities for storing, filling and handling liquids hazardous to water, the information and specifications of the general building inspectorate approval apply, in particular with regard to limiting cracks < 0.2 mm.

- **Substrate preparation**
Prepare the substrate by suitable means, e.g. steel ball jetting or diamond grinding, so that it meets the requirements specified above.
Broken out or missing areas in the substrate should be filled flush with the surface using Remmers PCC systems or Remmers EP mortars.

Production of the mixture



- **Combi-container**
Add the entire quantity of the hardener (component B) to the base compound (component A).
Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).
Pour the mixture into a separate container and mix again thoroughly.
Mix for at least 3 minutes.
Insufficient mixing is indicated by streaks forming.

Mixing ratio (A : B)	75 : 25 parts by weight
-----------------------------	-------------------------

In the case of filled systems, slowly stir the corresponding quantity of filler into the reaction resin mixture and mix thoroughly.

As soon as the mixture is ready to use, apply all of it to the prepared surface and spread it using a suitable tool.

Directions



For professional users only!

- **Conditions for use**
Temperature of the material, air and substrate: from min. +10 °C to max. +30 °C.
During the curing process, the applied material should be protected from moisture which could impair the surface and impair the adhesion.
Relative humidity should not exceed 80%.
The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.
- **Working time (+20 °C)**
approx. 25 minutes
- **Waiting time (+20 °C)**
Waiting times between coats should be at least 12 hours and max. 48 hours.
If waiting times are longer due to site conditions, the surface of the previous coat must be broadcast in a specific manner with fire-dried quartz sand (e.g. grain size 0.3-0.8 mm) while fresh or sanded back until stress-whitening begins to occur before proceeding to the next step.
- **Drying time (+20 °C)**
Foot traffic after 1 day, mechanical loading after 3 days, full loading capacity after 7 days.

As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Application examples

- **Priming**
Apply the mixed resin generously to the surface. Distribute with a suitable tool, e.g. rubber blade, and work into the substrate with an epoxy roller so that pores in the surface of the substrate are completely filled.
It may be necessary to apply several layers.

Application rate	Approx. 0.30 - 0.50 kg/m ² binder (depending on the substrate)
-------------------------	---



- Levelling layer/scratch coat
Pour the material, filled with a ratio of up to 1 : 1.5 parts per weight on the previously prepared surface, distribute with a suitable trowel and, if needed, roll over with a spiked roller.

Application rate	Per mm layer thickness of base layer: approx. 0.85 kg/m ² binder and 0.85 kg/m ² quartz sand (grain size 0.1 - 0.4 mm)
------------------	--

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C). Slight deviations from these values may arise if the product is worked with on site. Primers must always be applied so that all pores are filled; it may therefore be necessary to increase the application rate or to apply a second coat.

As mineral substrates have different absorption capacities, impregnated surfaces have a spotted appearance. Not suitable for high-visibility surfaces.

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.

Abrasive mechanical loads leave traces of wear.

Epoxy resins are generally not colourfast when exposed to UV light or weather.

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

For the installation of systems that are subject to approval, the directions contained in the relevant approval must be observed.

Tools / Cleaning




Smoothing trowel, notched trowel, notched scraper, rubber scraper, epoxy roller, spiked roller, mixing device (compulsory mixer if necessary)

More detailed information can be found in the Remmers Tool Programme.
Clean tools, equipment and splashed material immediately while fresh with V 101 Thinner.
Take suitable protective and waste disposal measures when cleaning.

Remmers tools
➤ [Patentdispenser \(4747\)](#)

Storage / Shelf life



If stored unopened in the original container and kept cool, dry and protected from frost, min. 12 months (component A)/min. 24 months (component B).

Safety data / Regulations

For professional users only!
For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet and the brochure entitled "Epoxy Resins in the Construction Industry and the Environment", issued by Deutsche Bauchemie e.V. (2nd edition 2009).

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/j): max. 500 g/l (2010).
This product contains < 500 g/l VOC.

Declaration of performance

➤ [Declaration of performance](#)



Declaration of conformity



Remmers GmbH (CE)

Bernhard-Remmers-Str. 13, D – 49624 Lönningen

Remmers (UK) Limited (UKCA)

Unit 4, Lloyds Court, Manor Royal Crawley, RH10 9QU

10 (CE); 23 (UKCA)

GBIII 011_4

EN 13813:2002

1427

Synthetic resin screed for use internally in buildings

Reaction to fire:	E _{fl}
Release of corrosive substances:	SR
Wear resistance:	≤ AR1
Bond strength:	≥ B1.5
Impact resistance:	≥ IR4

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.