





Mounting Foam 1K

1-component moisture-hardening PU foam for insulating, bonding & filling



	Availability		
	Quantity per pallet	672	
	Size / Quantity	12 x 500 ml	
	Container code	12	
	Art. no.		
	1586		
Application rate	Dependent on application		
depending on application	Yield: for 500 ml: approx. 15 l/can (free-foaming) Apply to a large enough trial area to determine the precise amount required.		
	Apply to a large enough trial a	irea to determine the precise amount required.	
lange of use		g work during interior construction (building material class B2 according to DIN	
	4102)		
	 Assembly of door and window frames Filling and waterproofing cavities and joints 		
		nasonry, wood, sheet metal and various plastics	
Property profile	Specially designed for application without guns		
	High foam yield		
	 Excellent isolation, sound and heat insulation Rot-proof 		
	Resistant to soft rot		
	Resistant to water, oil, petrol,	alkalis and various solvents	
Characteristic data of the product	On delivery		
	Colour	Champagne	
	Expansion	Approx. 200%	
	Once fully cured		
	Density (20 °C)	Approx. 25 kg/m ³	
	Tensile strength	Approx. 7 N/cm ²	
	Temperature resistance	Approx40 °C to +90 °C	
	Thermal conductivity λ	0.035 W/(m•k)	
	Reaction to fire (DIN 4102)) B2	
	The values stated represent typical	characteristic data of the product and are not to be understood as binding product specification	
	> Allg. bauaufs. Prüfzeugnis (32 - DIN 4102)	
Certificates			
	Substrate requirements		
	-	om dirt, dust, loose parts, oil and grease deposits.	
	-	om dirt, dust, loose parts, oil and grease deposits.	
	The substrate must be free fr Substrate preparation Thoroughly moisten the subst	trate.	
Certificates Preparation	The substrate must be free fr Substrate preparation	trate.	



Directions	Conditions for use Temperature of the material, air and substrate: from min. +5 °C to max. +35 °C.	
JF ≥-5°C	Use the material according to the applicable regulations.	
Tips on use	Do not use on fire doors.	
	 Drying Tack-free: after 20 minutes (at +20 °C) Can be cut: after 45 minutes (at +20 °C) Load-bearing: after 24 hours (at +20 °C) 	
Notes	Always set up a trial area/trial areas first. Do not heat can to above +50 °C. The applicable regulations and legal requirements must be observed. The relevant test certificates must be observed when planning and carrying out work.	
Tools / Cleaning	Hardened foam is insoluble. Remove impurities immediately with foam cleaner.	
Storage / Shelf life	If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.	
Safety data / Regulations	For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.	
Personal protective equipment	Use a type A respiratory filter (brown) during application.	
Disposal	Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.	

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.