



## Induline LW-715E

Water-based, varnishing intermediate and final coat especially suited to electrostatic spraying



Colour	Availability					
	Quantity per pallet	96	22	4	4	1
	Size / Quantity	2 x 5 l	20 l	90 l	120 l	1000 l
	Type of container	Tin bucket	Tin bucket	Plastic drum	Plastic drum	Plastic container
	Container code	05	20	90	68	61
	Art. no.					
<b>Induline LW-715E/05 UV+ cloth matt</b>						
clear	1799		■		■	■
special colours	1819	■	■		■	
<b>Induline LW-715E/20 UV+ matt</b>						
clear	1768	■	■			
special colours	1769	■	■			
<b>Induline LW-715E/20 matt</b>						
clear	1823	■	■		■	■
special colours	1824	■	■	■	■	■
<b>Induline LW-715E/30 UV+ silk matt</b>						
clear	1798		■		■	
special colours	1807		■		■	
<b>Induline LW-715E/40 silk gloss</b>						
clear	1759	■	■		■	■
special colours	1758	■	■		■	■

### Application rate

150 - 275 ml/m<sup>2</sup> (plus spraying loss)  
(corresponds to wet film thickness: 150 - 275 µm, dry film thickness: 50 - 100 µm)



### Range of use



- For use on interior and exterior wood
- Soft and hard woods
- Dimensionally stable wood building elements: e.g. windows and doors
- Protected constructions: e.g. wood-aluminium windows
- Intermediate and finishing coats
- Single coat and multi-coat procedure
- Electrostatic and non-electrostatic spray application
- For use by professionals

### Property profile



- Good flow properties
- High level of UV resistance and colour stability
- Block resistant (in accordance with Code of Practice HO.03)
- Pleasant feel
- High brilliance
- Special combination of binding agents creates an extremely hard-wearing surface



Characteristic data of the product	Viscosity (20 °C; 29 s-1)	Approx. 2500 mPas
	Binder	Spec. PU/acrylate polymers
	Density (20 °C)	Approx. 1.04 g/cm <sup>3</sup>
	Odour	Characteristic
	Degree of gloss	Cloth matt / matt / silk matt / silk gloss

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates > [French VOC Emission Test](#)

Possible system products > [Induline SW-900\\* \(3776\)](#)  
> [Induline GW-306\\* \(3488\)](#)  
> [Induline GW-360 \(3201\)](#)  
> [Induline ZW-502i \(1633\)](#)  
> [Induline ZW-504i \(3453\)](#)  
> [Induline ZW-507i \(1636\)](#)  
> [Induline SW-935 \(3786\)](#)  
> [Induline GW-390 \(7950\)](#)  
> [Induline Mix & Go Brushing Additive \(3246\)](#)


\*Use biocidal products carefully.  
Always read the label and product information before use.

Preparation ■ **Substrate requirements**  
The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner. Dimensionally stable wood building elements: wood moisture content 11-15%

■ **Substrate preparation**  
If necessary, impregnate non-resistant woods with a wood preservative\* (\*Use biocides safely. Always read the label and product information before use).  
Pre-treat using a suitable primer & intermediate coat and carry out intermediate sanding if necessary.  
If necessary, protect parapet joints with Induline V-Joint Protection or Induline AF-920.

Directions ■ **Conditions for use**  
Temperature of the material, air and substrate: from min. +15 °C to max. +30 °C.

The values given are based on undiluted material. The best spraying pattern is achieved if the material has a temperature of 15-20 °C.  
Stir well.  
Airless spraying: nozzle size: 0.28-0.33 mm; material pressure: 70-90 bar.  
Air-mix spraying: nozzle size: 0.28-0.33 mm; material pressure: 70-90 bar, atomiser air pressure 1-2 bar.  
Seal opened containers well and use contents as soon as possible.



Tips on use ■ **Drying**  
Dust-dry: after approx. 1 hour  
Ready for sanding and overcoating: after approx. 4 hours  
Practice values at 23 °C and 50% relative humidity and a wet film thickness of 150 - 175 µm  
If forced drying is used, can be sanded and overcoated: after 20 minutes flash-off zone (at approx. 20 °C and 65 - 75% RH) / 75 minutes drying phase (approx. 45 °C, 1 m/s air circulation) / 20 minutes cooling phase  
If the temperature goes below the specified working temperature or exceeds the specified atmospheric humidity or maximum coat thickness, this will delay full drying and lead to inclusion of hydrophilic emulsifiers. This increases the risk of temporary water staining. This effect is reduced as the coat continues to harden.

■ **Thinning**





If necessary with water (max. 5%).


**Notes**

**Sealing:**  
Sealing compounds must be compatible with the coating and may only be applied once the coating has dried thoroughly.  
Only use sealing profiles that are free of plasticisers.

**Production of a brushing quality:**  
This product can be used with Induline Mix & Go to produce an easy-to-apply lacquer for reconditioning and repair work.


**Care and maintenance:**  
Wood is subjected to great climatic and environmental stresses when outdoors. The coat is susceptible to the processes of natural ageing, wear and decomposition. Decomposition takes place at different speeds, depending on the stress (weak, average, strong) placed on the wood building element. Weathering stages may vary according to the part or element affected. To give wood the longest and best possible protection it is advisable to examine surfaces every year. Any damage found should be addressed immediately after cleaning.  
For cleaning and care, we recommend the care set for windows (2745) and doors (2746).  
Use Aqua HSL-35 and Aqua DSL-55 or HSL-30 and MSL-40 to carry out repairs.  
Observe current standards and guidelines for coating wood building elements outdoors (Codes of Practice issued by the German Association of Window and Facade Manufacturers (VFF), Code of Practice No. 18 issued by the German Federal Committee for Paint and the Protection of Material Assets (BFS), guidelines issued by the German Lacquer and Printing Ink Association (VdL) and ift guidelines issued by the Institut für Fenstertechnik).

**Tools / Cleaning**



Manual spray gun, automatic spray systems, electrostatic systems  
Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use.  
Ensure that any residue from cleaning is disposed of correctly.

**Storage / Shelf life**



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

**Safety data / Regulations**

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

**Personal protective equipment**

Respiratory protection with at least an A/P2 combination filter must be worn during spraying, together with safety goggles. Wear suitable protective gloves and clothing.

**Disposal**

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

**Biocidal Products Regulation**

Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!

**VOC content as per the "Decopaint" Directive (2004/42/EC)**

EU limit value for the product (Cat. A/e): max. 130 g/l (2010).  
This product contains < 130 g/l VOC.

VOC	
Kat. A/e	2010: 130g/l
max.:	130g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.