



PU Wood Substitute Compound

Solvent-free resin component for reconstructing interior and exterior wood

Availability	
Quantity per pallet	84
Size / Quantity	
Container code	05
Art. no.	
2386	■

Application rate Per 1 litre volume for reconstruction: 0.5 kg PU wood substitute compound and 0.25 kg wood shavings

Range of use



- For reconstructing wood building elements
- Beams in framework
- Beam end repairs
- Laminated wood
- Window renovation
- For use by professionals

Property profile

- Wood effect
- Water vapour permeable
- High compressive strength
- Can be overcoated

Characteristic data of the product

Density (20 °C)	Approx. 1.13 g/cm ³
Odour	Mildly aromatic

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products


- Rofalin Acrylic (2330)
- Aqua OWF-68/tm Weather Protection Oil Woodstain ^[ecol] (7740)
- Aqua OML-48/tm Medium Build Oil Stain ^[ecol] (7710)
- Aqua VL-66/sm-Venti Coat 3in1 (7090)
- Aqua DL-65 Top PU (7200)
- Aqua MSL-45/sm Medium Build Stain UV+ (7130)
- HSL-30/m Premium Wood Protection Stain 3in1* (7100)
- Aqua HSL-35/m Premium Wood Protection Stain 3in1* (7120)
- Aqua DSL-55 High Build Stain PU (7220)
- MSL-40/sm Medium Build Stain UV+ (7240)

*Use biocidal products carefully.
Always read the label and product information before use.

Preparation

- **Substrate requirements**
The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.
Permitted wood moisture content: u < 18%
- **Substrate preparation**
Create a stable mould (e.g. laminated board) in the original dimensions of the wood building element and line with release paper.
For larger batches (> 3 kg), the mould must also be secured with screw clamps. Do not exceed the maximum batch size of 7.5 kg (risk of bursting).


Production of the mixture



- **Mixing**
2:1 with wood shavings (permitted wood moisture 8-12%, chip size < or = 1 mm) by weight (1:2 by volume).
Mix the material with the wood shavings for at least 3 minutes until a pourable consistency is obtained.
Working time max. 10 min; this may be lower at high temperatures.



Directions



■ Conditions for use

Temperature of the material, air and substrate: from min. +10 °C to max. +25 °C.

Pour the compound into the void, compact with a trowel, cover with release paper and seal tightly.
Remove the mould after 24 hours.

Reconstructed areas can be sanded and provided with decorative coatings after 7 days.

Tips on use

During application, do not allow any additional moisture to enter the reaction process.
Protect the product from moisture.

■ Drying

Overcoating: after 7 days

Notes

If the safety of load-bearing and bracing wooden components is compromised, a structural engineer must be consulted. To help the structural engineer on site, a statics model has been developed to aid with dimensioning (rod dowels, flat steel thickness) during renovation.

Tools / Cleaning


Trowel



Clean tools immediately after use with V 101 Thinner. Dispose of the remains from cleaning properly.
The material can no longer be cleaned off once it has dried or hardened.

Storage / Shelf life

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 6 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.