



## OB-008 Oil Stain

Solvent-based linseed oil stain with a very long open time



Colour	Availability		
	Quantity per pallet	640	96
	<b>Size / Quantity</b>	<b>1 l</b>	<b>5 l</b>
	Type of container	Tin bucket	Tin bucket
	Container code	01	05
	<b>Art. no.</b>		
clear (pre-filling: 90%)	2787	■	
brilliant white (RC-995)	2788	■	
nutwood (RC-660)	2789	■	
light oak (RC-365)	2790	■	
teak (RC-545)	2791	■	
ebony (RC-790)	2792	■	
silver grey (RC-970)	2793	■	
special colours	2794	■	■

### Application rate

40 - 80 ml/m<sup>2</sup>



The application rate is highly dependent on the absorbency of the wood and the final sanded finish. After every application, remove excess material with a lint-free cotton cloth after approx. 20-30 minutes.

### Range of use



- Especially for use on softwoods and large-pored woods (e.g. oak)
- For use under finishes on an oil, wax or alkydic resin base
- Wooden floors and stairs
- Furniture and interior finishing work
- Alone: as impregnation/tinting oil on surfaces with low loading
- For use by professionals

### Property profile



- Ready-for-use base colours that can be mixed with each other
- Long open time for streak-free application (on large surfaces)
- Intense colour
- Made from renewable raw materials (linseed oil and natural resin)
- Cobalt-free and MEKO-free

### Characteristic data of the product

Binder	Linseed oil/natural resin
Density (20 °C)	Approx. 0.82 g/m <sup>3</sup>

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

### Certificates

- [Approval as surface coating system for parquet and wooden flooring](#)

### Additional information

- [Colour card](#)
- [Applying oil-based products with a cloth](#)

### Possible system products

- [HWS-112 Hard Wax Seal \(1826\)](#)
- [HSO-118 High Solid Oil \[eco\] \(7708\)](#)



➤ **Aqua HWS-712 Hard Wax Seal <sup>[eco]</sup> (5290)**

**Preparation**

■ **Substrate requirements**

The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.

Wood moisture content: 8-12%

■ **Substrate preparation**

Thoroughly remove any dirt, grease and non-adhering old coatings.

Wash off greasy or resin-rich woods/substrates with WV-891 or V-890. Use UN-894 indoors on the construction site. Ensure good ventilation for solvents.

Sand wood with P 80 - 150.

The coarser the sanded finish, the more intense the colouring in pigmented varieties will be.

**Directions**



■ **Conditions for use**

Temperature of the material, air and substrate: from min. +18 °C to max. +25 °C.

Stir well.

Application by roller, brush, spreader or pad.

Remove any excess material using a lint-free cotton cloth after approximately 20-30 minutes.

Seal opened containers well and use contents as soon as possible.

**Tips on use**



Check colour, adhesion and compatibility with the substrate by setting up a trial area.

Before coating technically modified woods and wood-based materials, apply the coating to a trial surface and conduct a suitability test on the desired area of use.

Ensure good ventilation.

Risk of self-ignition (DGUV information brochure 209-046).

The product should not be applied at the same work stand as NC-based varnishes or stains. Collect any textiles soiled with the product (e.g. cleaning rags, work clothing) in fire-resistant waste containers and dispose of properly.

■ **Drying**

Dust-dry: after approx. 4 hours

Can be overcoated by spraying: after approx. 6 hours

Can be overcoated using a roller: after approx. 14 hours

Practice values at +20 °C and 65% relative humidity.

Low temperatures, poor ventilation and high humidity delay drying.

■ **Thinning**

If necessary, dilute with max. 2% Thinner V 101. OB-008 Oil Stain (clear) is the base material for thinning and for adjusting/reducing the colour intensity.

**Notes**

Oil-based products contain natural ingredients. Under the influence of UV light, exclusion of light (dark yellowing), heat or individual changes in the wood, these can lead to a change in the surface. The surfaces therefore require special care. Please refer to the information sheet on general application instructions for oils and waxes. White, pastel and grey tones can lose their intensity within a short period of time. This happens depending on the type of wood used, substances contained in the wood, exposure to light and heat. If these changes are not desired, a stained and lightfast lacquered surface finish is recommended.

**Tools / Cleaning**



Flat brush, short-pile (3-5 mm) velour or mohair roller, rotary disc machine with white non-abrasive pad, wadded rag/lint-free cotton cloth, stainless steel/spring spatula.


Clean tools immediately after use with V 101 Thinner.

Ensure that any residue from cleaning is disposed of correctly.

**Remmers tools**

➤ **Federspachtel (4788)**

**Storage / Shelf life**



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months.

**Safety data / Regulations**

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

**Disposal**

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.