



Colorfuge EP

Colour	Availability		
	Quantity per pallet	200	60
	Packaging unit	10 x 1 kg	5 kg
	Type of container	Tin bucket	Tin bucket
	Container code	01	05
	Art. no.		
	2861	■	■
	2862	■	■

Range of use ■ [AW_GR_220]

Property profile ■ Thixotropic
 ■ Resistant to chemicals
 ■ [EG_GR_97]


Possible system products > WHG TX (1221)
 > FL fix (2817)

Preparation ■ **Substrate requirements**
 The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.
 [U1_B_100]

Production of the mixture ■ **Combi-container**
 Add the entire quantity of the hardener (component B) to the basic compound (component A).
 Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).
 The mixing time must be at least 2 minutes.
 Pour the mixture into a separate container and mix again thoroughly.
 Insufficient mixing is indicated by streaks forming.



Directions For professional users only!



[VA_B_71]



Tips on use

As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

[U1_B_101]

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.

[H_B_179]

[H_B_180]

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C) using standard colours. Slight deviations from these values may arise if the product is worked with on site.

Epoxy resins are generally not colourfast when exposed to UV light or weather.

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

Tools / Cleaning


Wash tools and any splashed material with water immediately and while wet.

[H_B_173]



Storage / Shelf life

If stored unopened in the original container and kept cool, dry and protected from frost, min. 12 months (component A)/min. 24 months (component B).



Safety data / Regulations

For professional users only!

Further information concerning safety during transport, storage and handling as well as on disposal and ecology can be found in the latest Safety Data Sheet.

Personal protective equipment

This information can be obtained from the current Safety Data Sheets and/or the relevant professional associations.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.