



VZ MB

Liquid retarder

Availability	
Quantity per pallet	360
Size / Quantity	
Type of container	Plastic bottle
Container code	01
Art. no.	
3005	■

Application rate Max. 1.0% for MB 2K based on total quantity
Max. 0.5% for Betofix OS 5b+ based on total quantity

Range of use ■ Delaying the setting rate

Property profile ■ Retarding and liquefying effect

Characteristic data of the product	Density (20 °C)	Approx. 1.02 g/cm ³
	Consistency	Fluid
	Appearance	Clear liquid

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products

- MB 2K (3014)
- Betofix OS 5b+ (1113)

Directions ■ **Conditions for use**
Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.

Add to the liquid component while stirring gently.
Max. quantity to be added: 250 ml per 25 kg container of MB 2K
Max. quantity to be added: 125 ml per 25 kg container of Betofix OS 5b+
Retarding effect at 30 °C up to 100 min.



Notes Deviations from applicable regulations must be agreed separately.
The relevant test certificates must be observed when planning and carrying out work.

Storage / Shelf life If stored in unopened original container in a cool, dry place, protected from frost, the product will keep for at least 9 months.





Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.