



Bleach for Softwoods

Special liquid bleaching agent to combat wood discolouration


Availability		
Quantity per pallet	288	75
Size / Quantity	1 l	5 l
Type of container	Plastic bottle	Plastic bottle
Container code	81	88
Art. no.	3152	■
		■

Application rate 100 - 200 ml/m² depending on the level of discolouration



Range of use

- Wood and wood-based materials
- For use by professionals



Property profile

- Brightening effect
- Bleaches discoloured wood




Preparation

- Substrate preparation
Fully remove any existing old coatings.

Directions

- Conditions for use
Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.

Brush generously onto the discoloured area.
Repeat the process if necessary.
Wash off residue thoroughly with water.
Once fully dry, the wood can be treated with stains or paints.
Seal opened containers well and use contents as soon as possible.



Tips on use

- Drying
Can be overcoated: after approx. 2.5 - 4 hours

Practice values at +20 °C and 65% relative humidity.
Low temperatures, poor ventilation and high humidity delay drying.
- Thinning
Ready to use



Tools / Cleaning

- Brush


Clean tools immediately after use with water.
Ensure that any residue from cleaning is disposed of correctly.





Storage / Shelf life

If stored in unopened original container in a cool, dry place protected from frost, the product will keep for at least 1 month.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.