



Aqua OVL-49/tm Grey Stain Oil [eco]

Durable grey stain made from renewable raw materials for interior and exterior wood in sensitive areas




Colour	Availability		
	Quantity per pallet	200	22
	Size / Quantity	2 x 2,5 l	20 l
	Type of container	Tin bucket	Tin bucket
	Container code	03	20
	Art. no.		
clear	3214	■	■
Base M	3213	■	■
special colours	3215	■	■

Application rate

Approx. 80 - 100 ml/m² per coat
Min. 2 coats



Range of use



- For use on interior and exterior wood
- Dimensionally stable wood building elements: e.g. windows and doors
- Wood building elements with limited dimensional stability, e.g. folding shutters, matchboarding, summerhouses
- Wood building elements with no dimensional stability: e.g. fences, framework, carports, planking
- Wooden beehives, bee boxes and other wooden elements used in beekeeping
- Playground equipment
- Sustainable building suitable for building certifications DGnB, LEED, BNB
- Not suitable for coating flooring (terraces, wooden decking, etc.)
- For use by professionals

Property profile



- Water-based with a very low solvent content
- Natural grey tones for wood
- Even colour tone across areas exposed to weathering and areas sheltered from weathering
- Made from at least 80% renewable raw materials
- Bee-friendly formula
- Non-drip
- Good flow properties
- Breathable
- A vegan product based on the information available to us
- Classified as non-spontaneously combustible according to EPH test report*

Characteristic data of the product

Binder	Based on plant oils and biomass-balanced binder
Density (20 °C)	Approx. 1.02 g/cm ³
Odour	Mild
Degree of gloss	Cloth matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- [DIN EN 71-3 Migration of certain elements](#)

Test standards

Low emissions according to the AgBB scheme

Additional information

- [Sustainability data sheet](#)



Possible system products

- Aqua IG-15 Impregnation Primer IT* (7145)
- Wood Impregnation [eco] (0652)
- Induline SW-910 (3777)

*Use biocidal products carefully.
Always read the label and product information before use.

Preparation

■ **Substrate requirements**

The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.

Wood building elements with limited or no dimensional stability: wood moisture content max. 18%

■ **Substrate preparation**

Thoroughly remove any dirt, grease and non-adhering old coatings.

Sand grey and weathered wood surfaces down to sound, bright wood.

Remove any loose and torn knots as well as resin that bleeds from the wood and clean with a suitable product (e.g. V 101 Thinner, a nitrocellulose or universal thinner).

In order to avoid the use of wood preservatives as far as possible, the construction should be designed to be water-repellent (avoid horizontal surfaces, open end-grain wood, capillary joints, water and moisture accumulation points, contact with splash water, sharp edges). Pre-treatment with Wood Impregnation [eco] improves the hydrophobic effect.

Exterior wood that needs to be protected against soft rot and blue stain must be pre-treated with a suitable wood preservative* - not necessary for interior wood (*Use biocides safely. Always read the label and product information before use).

Thoroughly sand any old coatings that are still intact.

Observe BFS Code of Practice No. 18 "Coatings on Wood and Wooden Working Materials in Outdoor Areas".

Directions



■ **Conditions for use**

Temperature of the material, air and substrate: from min. +10 °C to max. +25 °C.

Stir well.

Application by brush, spraying

Apply in the direction of the grain.

Flow cup gun: nozzle size: 2.0 - 2.5 mm; atomiser air pressure: 2.0 - 3.0 bar.

Air-mix spraying: nozzle size: 0.28-0.33 mm; material pressure: 70-90 bar, atomiser air pressure 1-2 bar.

Airless spraying: nozzle size: 0.28-0.33 mm; material pressure: 90-120 bar.

Apply 2 coats with light intermediate sanding in between.

Apply a further coat if required.

Protect end-grain surfaces against water ingress by applying multiple coats of the material in the corresponding colour. Alternatively, coat the end-grain surfaces with Induline SW-910 before applying the final coat.

Use material with the same batch number on contiguous surfaces (mix material of different batches beforehand), otherwise slight differences in colour, gloss and texture may occur.

Seal opened containers well and use contents as soon as possible.

Tips on use



Check colour, adhesion and compatibility with the substrate by setting up a trial area.

Before coating technically modified woods and wood-based materials, apply the product to a trial surface and conduct a suitability test on the desired area of use.

Pre-testing is recommended also on other woods.

Areas that are being coated or dried should be protected against rain, wind, sunlight and condensation.

In principle, the product is also suitable for use on wood rich in substances (e.g. oak, robinia, acacia).

However, reactions with the water-soluble substances in the wood may occur that result in discolouration of the coating film and thus an impaired optical appearance (this is particularly true of white and grey shades).

Rainfall may cause water soluble substances to bleed from wood that is rich in such substances, e.g. oak, red cedar, afzelia, redwood, etc. This may lead to the discolouration of light-coloured masonry or render.

■ ***Information about self-ignition**

In external tests, the tested product exhibited significantly lower reactivity than conventional reference products that dry by oxidation. The risk of self-ignition is therefore classified as lower.

It should be noted that the tests carried out by EPH could not take into account all possible scenarios that might occur in practice. For example, contact of objects and media contaminated with this product, such as rags or dust, with other highly flammable agents, such as dust containing cellulose nitrate or certain solvents, could lead to conditions that result in ignition.

Avoid excessive overspray.

Leave fresh spraying dust to dry before sweeping up.

Collect spray mist in fireproof waste containers and spray regularly with water to prevent self-ignition of the spray mist, especially if large quantities accumulate.

■ **Drying**

Dust-dry: after approx. 1 hour

Ready for overcoating: after approx. 4 hours



Practice values at +20 °C and 65% relative humidity.
 Low temperatures, poor ventilation and high humidity delay drying.
 Drying may take longer depending on the type of wood, e.g. oak, due to substances it contains.

- **Thinning**
 Ready to use

Notes

DIN EN 71-3 "Migration of certain elements":
 This product complies with the limits for the migration of heavy metals to children's toys according to DIN EN 71-3 and thus fulfils one of several further requirements for the safety of children's toys according to the EU "Toy Directive" (2009/48/EC).

On planed larch and softwoods with a high resin content, the coating may have reduced adhesion and resistance to weathering. This is especially the case on horizontal year rings, knots and areas of winter growth that are high in resin. Maintenance and renovation must be carried out more frequently on these surfaces. The only remedy for this is pre-weathering or very coarse sanding (P80). If these wood types are rough-sawn, considerably longer maintenance and renovation intervals are to be expected.
 Observe the regulations concerning design principles for wood protection.
 Do not use on horizontal surfaces without drainage slopes and without edge radius, avoid accumulated moisture.
 Colour deviations may occur with mica shades in comparison with printed colour charts, during touch-up work and with different application methods. Different batches of the same product should be mixed. Colour deviation according to BFS data sheet no. 25 Appendix A.3.

Tools / Cleaning


Paintbrush with synthetic bristles, flat brush, flow cup gun, airless/airmix spraying equipment



Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use.
 Ensure that any residue from cleaning is disposed of correctly.

Storage / Shelf life

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Personal protective equipment

Respiratory protection with a particle filter P2 must be worn during spraying, together with protective goggles. Wear suitable protective gloves and clothing.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Biocidal Products Regulation

Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (cat A/e): max. 130 g/l (2010).
 This product contains < 20 g/l VOC.

VOC	
Kat.	A/e
2010:	130g/l
max.:	20g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.