



Induline SW-961

- Premium Hydro Formwork Support Coating -

Water-based concentrate with film preserver for coating formwork supports


Colour	Availability		
	Quantity per pallet	1	1
	Size / Quantity	600 kg	1000 kg
	Type of container	Container	Container
	Container code	63	61
	Art. no.		
premium yellow	3287	■	■

Application rate

50 - 80 ml/m² depending on the absorbency of the substrate (ready-to-use solution)



Range of use



- For use on exterior wood
- Coating of formwork beans made of wood and wood-based materials
- Edge coating for wood-based materials (e.g. formwork panels)
- For use by professionals

Property profile



- Concentrate
- Film preserver protects against microbial damage
- High colour intensity
- Can be stacked wet-on-wet
- Alkali-resistant
- Repels water

Characteristic data of the product

Binder	Acrylate
Density (20 °C)	Approx. 1.03 g/cm ³
Runout time s (20° C, DIN 4)	Approx. 30
Odour	Characteristic

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products

- [Induline SW-910 \(3777\)](#)

Preparation

■ Substrate requirements

The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.
Wood moisture content max. 15%

Production of the mixture


■ Mixing

Add tap water to the ready-to-use solution in the desired mixing ratio (max. 1:12) while stirring.
It is recommended to use a batching unit for automatic mixing.





Directions



■ **Conditions for use**

Temperature of the material, air and substrate: from min. +10 °C to max. +30 °C.

Stir well, including during application or after a break in work.
Industrial series production (VACUMAT®, board coating machine)
Seal opened containers well and use contents as soon as possible.

Tips on use




Check colour, adhesion and compatibility with the substrate by setting up a trial area.

■ **Drying**

Ready for overcoating: after approx. 1 hour
Practice values at +20 °C and 65% relative humidity.
Low temperatures, poor ventilation and high humidity delay drying.


Tools / Cleaning



Vacuum processing equipment, board coating machine

Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use.
Ensure that any residue from cleaning is disposed of correctly.

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Biocidal Products Regulation

Contains as "treated goods" a biocidal product (film preservative) with the biocidal active agent 3-iodo-2-propynyl butylcarbamate to protect the film from contamination by microbial organisms (algae, mould etc.). Always follow the directions carefully!

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/e): max. 130 g/l (2010).
This product contains < 130 g/l VOC.

VOC	
Kat.	A/e
2010:	130g/l
max.:	130g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.