



Induline GW-342 U

Water-based, translucent universal primer with film preserver

Colour	Availability			
	Quantity per pallet	96	22	4
	Size / Quantity	5 l	20 l	120 l
	Type of container	Tin bucket	Tin bucket	Plastic drum
	Container code	05	20	68
	Art. no.			
clear	3288	■	■	
special colour	3289	■	■	■


Application rate

80 - 120 ml/m² per coat

Depending on the application method, wood type and wood surface.



Range of use



- For use on exterior wood
- Soft and hard woods
- Dimensionally stable wood building elements: e.g. doors, windows and shutters
- Wood building elements with limited dimensional stability, e.g. folding shutters, matchboarding, summerhouses
- Wood building elements with no dimensional stability: e.g. fences, framework, carports, planking
- For use by professionals

Property profile



- Good (wet) adhesion
- Good pore wetting performance
- Good flow properties on stripped wood
- Good flow behaviour on raw and impregnated wood, especially on complex and overdimensioned components
- Ready to apply by dipping or flow-coating

Characteristic data of the product

Runout time s in ISO cup 3	24 - 26
Binder	Special resins
Density (20 °C)	Approx. 1.02 g/cm ³
Runout time s in DIN 4 cup	10-11

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.



Possible system products

- Induline ZW-504 LP (283383)
- Induline ZW-508 (1639)
- Induline LW-700/20 LP (281680)
- Induline LW-708/20 (1677)
- Induline LW-715E (1798)
- Induline ZW-502i (1633)
- Induline LW-720 (3996)
- Induline LW-700 (3400)
- Induline ZW-405 (283464)
- Induline ZW-408 (1638)
- Induline ZW-400 (3900)
- Induline DW-608/20 (1229)
- Induline ZW-507i (1636)
- Induline LW-790 (7960)

Preparation

■ Substrate requirements

The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.

Dimensionally stable wood building elements: wood moisture content 11-15%

Wood building elements with limited or no dimensional stability: wood moisture content max. 18%

■ Substrate preparation

If necessary, impregnate non-resistant woods with a wood preservative* (*Use biocides safely. Always read the label and product information before use).

Observe BFS Code of Practice No. 18 "Coatings on Wood and Wooden Working Materials in Outdoor Areas".

Directions



■ Conditions for use

Temperature of the material, air and substrate: from min. +15 °C to max. +30 °C.

Relative humidity: 40 % - 80 %.

Stir well, including during application or after a break in work.

Qualified specialist companies: brushing, dipping, flow-coating and spraying in closed systems only.

Once dry, apply further coatings.

Seal opened containers well and use contents as soon as possible.

Tips on use



Check colour, adhesion and compatibility with the substrate by setting up a trial area.

Before coating technically modified woods and wood-based materials, apply the coating to a trial surface and conduct a suitability test on the desired area of use.

Substances in oak may bleed, causing dark discolouration, when coated with water dilutable dispersion stains.

Dilute with up to 10% water to improve flow properties in unfavourable conditions (elevated temperatures, low humidity). Add water to make up for any moisture lost through evaporation.

If foam builds up in the flow coating facility, it is recommended to add 0.2 – 0.8 % VP 9325 defoaming agent, strength 2.

In summer we recommend adding 0.1% Antibak VP 20164 to opened containers after using in a flow coating facility.

■ Drying

Overcoating: after approx. 2.5 hours

Practice values at +20 °C and 65% relative humidity.



Low temperatures, poor ventilation and high humidity delay drying.

■ **Thinning**

Ready to use, dilute with water if necessary (max. 10%).

Notes

The system finder on our website www.remmers.com contains coating recommendations for specific wood types to be used when treating windows and exterior doors. Observe the information sheets "Upkeep and Maintenance of Dipping Tanks and Flow Coating Facilities" and "Information on Workplace Hygiene".

Tools / Cleaning


Paintbrush, dipping tank, flow coating facility, spraying equipment



Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use. Ensure that any residue from cleaning is disposed of correctly.

Storage / Shelf life

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Personal protective equipment

Respiratory protection with at least an A/P2 combination filter must be worn during spraying, together with safety goggles. Wear suitable protective gloves and clothing.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Biocidal Products Regulation

Contains as "treated goods" a biocidal product (film preservative) with the biocidal active agent 3-iodo-2-propynyl butylcarbamate to protect the film from contamination by microbial organisms (algae, mould etc.). Always follow the directions carefully!

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/e): max. 130 g/l (2010).
This product contains < 130 g/l VOC.

VOC	
Kat.	A/e
2010:	130g/l
max.:	130g/l



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.