



PUR Aqua Top 2K SG Plus

Transparent, slip-resistant, silk-gloss sealant



| Availability | | | |
|------------------------|---------------|-----------------------------|--|
| Quantity per pallet | | | |
| Size / Quantity | 2,5 kg | 10 kg | |
| Type of container | Tin bucket | Plastic bucket / Tin bucket | |
| Container code | 04 | 11 | |
| Art. no. | | | |
| 3632 | ■ | ■ | |

Application rate Approx. 0.13 kg/m²

Range of use ■ Slip-resistant sealing of EP and PU coatings in areas subject to low mechanical loads

Property profile ■ Silk gloss
 ■ Slip-resistant
 ■ Lightfast
 ■ Water vapour diffusion capable



Characteristic data of the product

| | Component A | Component B | Mixture |
|-------------------|------------------------|------------------------|------------------------|
| Density (20 °C) | 1.04 g/cm ³ | 1.15 g/cm ³ | 1.05 g/cm ³ |
| Viscosity (25 °C) | 445 mPa s | 4420 mPa s | 895 mPa s |

■ Once fully cured

| | |
|----------------------------------|------------------------------|
| Abrasion according to Taber test | 41 mg (CS10, 1000 U, 1000 g) |
| Solids content % by mass | 38 M-% |

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products


- Epoxy OS Color (6980)
- PUR Deco Color New (6674)
- Epoxy BS 3000 SG (6380)

Preparation

- Substrate requirements
The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.
The substrate must be prepared using suitable Remmers products.
- Substrate preparation
Apply the sealant within 48 hours. In the case of longer waiting times, sand the surface treated in the previous coat and remove dust.

Production of the mixture

- Combi-container
Add the entire quantity of the hardener (component B) to the base compound (component A).
Then, mix the compound thoroughly using a slow-turning electric stirrer (> 1500 rpm) and a Remmers patent disperser.
Pour the mixture into a separate container and mix again thoroughly.
Mix for at least 3 minutes.






Insufficient mixing is indicated by streaks forming.

| | |
|-----------------------------|------------------------|
| Mixing ratio (A : B) | 88:12 parts by weight. |
|-----------------------------|------------------------|

As soon as the mixture is ready to use, apply all of it to the prepared surface and spread it using a suitable tool.

Directions



For professional users only!

■ Conditions for use

Temperature of the material, air and substrate: from min. +10 °C to max. +25 °C.

During the curing process, the applied material should be protected from moisture which could impair the surface and impair the adhesion.

Relative humidity should not exceed 80%.

The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.

Good ventilation must be ensured so that water can be released into the air.

■ Working time (+20 °C)

approx. 60 minutes

■ Drying time (+20 °C)

Foot traffic after 8 hours, mechanical loading after 3 days, full loading capacity after 7 days.

The times given are reduced at higher temperatures and increased at lower temperatures, in particular in combination with high humidity.

Application examples

■ Sealant

Pour the material generously onto the surface. Use a suitable 25 cm epoxy roller to apply uniformly and generously, working crosswise, then roll using a 50 cm epoxy roller saturated with material. Replace the rollers with new ones every 30 minutes.

| | |
|-------------------------|---------------------------------------|
| Application rate | approx. 0.13 kg/m ² binder |
|-------------------------|---------------------------------------|

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C). Slight deviations from these values may arise if the product is worked with on site. Use sufficiently experienced personnel to ensure that surfaces are as even as possible.

Uneven application, strong draughts and large temperature differences on the surface can result in a non-uniform surface appearance due to differences in the degree of gloss.

Suitable for vehicle traffic with rubber tyres; not suitable for vehicle loads with metal or polyamide tyres nor for dynamic point loads.

Upon prolonged contact with a floor covering, coloured – and especially black – rubber can cause discolouration that cannot be removed (e.g. car tyres or machine bases). Suitable polyurethane wheels or underlay mats should be used in order to avoid such discolouration. Colourants, hair dyes, bleach and disinfectants can also cause discolouration if not removed immediately.

Maintenance measures are recommended in order to reduce the tendency to soil (see maintenance instructions).

Anti-slip floors naturally require more cleaning effort than smooth surfaces. Therefore, the use of cleaning machines with soft brushes is recommended.

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

Tools / Cleaning



25 cm epoxy roller, 50 cm epoxy roller, mixing apparatus

The Remmers patent disperser must be used as the stirring tool.

More detailed information can be found in the Remmers Tool Programme.


Clean tools, equipment and any splashed material immediately with water while still fresh.

Take suitable protective and waste disposal measures when cleaning.

Remmers tools

➤ [Patentdisperser \(4747\)](#)

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 6 months.

Safety data / Regulations

For professional users only!

Further information concerning safety during transport, storage and handling as well as on disposal and ecology can be found in the latest Safety Data Sheet.

Personal protective equipment

This information can be obtained from the current Safety Data Sheets and/or the relevant professional associations.



| | |
|---|--|
| Disposal | Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains. |
| Biocidal Products Regulation | Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully! |
| VOC content as per the "Decopaint" Directive (2004/42/EC) | EU limit value for the product (Cat. A/j): max. 140 g/l (2010). This product contains < 140 g/l VOC. |

Declaration of performance [▶ Declaration of performance](#)

Declaration of conformity



Remmers GmbH (CE)
Bernhard-Remmers-Str. 13, D – 49624 Lönningen
Remmers (UK) Limited (UKCA)
Unit 4, Lloyds Court, Manor Royal Crawley, RH10 9QU

09 (CE); 22 (UKCA)
GBIII 080
EN 13813:2002
3632

Synthetic resin screed for use internally in buildings

| | |
|----------------------------------|-----------------|
| Reaction to fire: | E _{fl} |
| Release of corrosive substances: | SR |
| Wear resistance: | ≤ AR 1 |
| Bond strength: | ≥ B 1.5 |
| Impact resistance: | ≥ IR 4 |

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.