



## remmers

## Induline SW-935

Water-based, clear impregnation, primer and sanding primer



| Colour | Availability        |              |              |
|--------|---------------------|--------------|--------------|
|        | Quantity per pallet | 96           | 22           |
|        | Size / Quantity     | 5 l          | 20 l         |
|        | Type of container   | Tin canister | Tin canister |
|        | Container code      | 05           | 20           |
|        | Art. no.            |              |              |
| clear  | 3786                |              |              |

Application rate

30 - 90 ml/m<sup>2</sup> per coat (depending on the area of application)



|       | _   |     |
|-------|-----|-----|
| Range | ofı | Jse |

| 📕 F | For u | ise on | interior | and | exterior | wood |
|-----|-------|--------|----------|-----|----------|------|
|-----|-------|--------|----------|-----|----------|------|

| Possible system products              | <ul> <li>Induline GW-360 (3201)</li> <li>Induline GW-390 (7950)</li> </ul>                                                        |                                                                                                    |  |
|---------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------|--|
| Additional information                | <ul> <li>Information on workplace hygiene</li> <li>Upkeep and maintenance of dipping tanks and flow coating facilities</li> </ul> |                                                                                                    |  |
| Certificates                          | > French VOC Emission Test                                                                                                        |                                                                                                    |  |
|                                       | The values stated represent typical o                                                                                             | characteristic data of the product and are not to be understood as binding product specifications. |  |
|                                       | Odour                                                                                                                             | Characteristic                                                                                     |  |
|                                       | Density (20 °C)                                                                                                                   | Approx. 1.005 g/cm <sup>3</sup>                                                                    |  |
| P. 0 0 0 0 0                          | Binder                                                                                                                            | Acrylate copolymer/alkyd emulsion                                                                  |  |
| Characteristic data of the<br>product | Runout time s in ISO cup 3                                                                                                        | Approx. 22-24                                                                                      |  |
|                                       |                                                                                                                                   | m to be removed during the first sanding operation<br>n combination with coloured primers          |  |
| H <sub>2</sub> 0                      | Strengthens wood                                                                                                                  |                                                                                                    |  |
| Property profile                      | <ul> <li>Quick and easy to use</li> <li>Quick-drying and easy to sand</li> </ul>                                                  |                                                                                                    |  |
|                                       | Wood building elements with l                                                                                                     |                                                                                                    |  |

Induline GW-209 (2498)
 Induline GW-201 (2491)
 Induline ZW-400 (3900)
 Induline ZW-425 (7918)
 Induline OW-800 (3463)
 Induline OW-810 (3461)





|                                                                                    | <ul> <li>Induline LW-720 (3996)</li> <li>Induline LW-721/05 (5105)</li> <li>Induline LW-722 <sup>[eco]</sup> (5100)</li> </ul>                                                                                                                                                                                                                                                                                                                               |  |  |
|------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|--|
| Preparation                                                                        | Substrate requirements<br>The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.<br>Dimensionally stable wood building elements: wood moisture content 11-15%<br>Wood building elements with limited or no dimensional stability: wood moisture content max. 18%                                                                                                                                   |  |  |
| Production of the mixture $ \begin{array}{c}                                     $ | <ul> <li>Mixing</li> <li>Undiluted: primer for aluminium-clad wood windows</li> <li>1:1 with water: impregnation with no active ingredients</li> <li>1:3 with water: washing aid</li> </ul>                                                                                                                                                                                                                                                                  |  |  |
| Directions                                                                         | <ul> <li>Conditions for use<br/>Temperature of the material, air and substrate: from min. +15 °C to max. +30 °C.</li> <li>Stir well, including during application or after a break in work.</li> <li>Application by brush, dipping, flow coating, spraying.</li> <li>Once dry, apply further coatings.</li> <li>Cannot be used as a replacement for wood preservative.</li> <li>Seal opened containers well and use contents as soon as possible.</li> </ul> |  |  |
| Tips on use $4^{h}$                                                                | Check colour, adhesion and compatibility with the substrate by setting up a trial area.<br>The best flow results on Accoya, oak and chestnut are achieved at a pH value of 9.0–9.5, corresponding to an<br>additive content of 0.3–0.5% VP 20829 Additive (0366).<br>If foaming occurs in the flow coating system, it is recommended to add 0.2-1.0% VP 9325 defoaming agent - strength<br>2.                                                                |  |  |
|                                                                                    | Drying<br>Dust-dry: after approx. 30 minutes<br>Overcoating: after approx. 4 hours<br>(at 23 °C and 50% RH)                                                                                                                                                                                                                                                                                                                                                  |  |  |
|                                                                                    | <ul> <li>If force drying is used, can be overcoated: after approx. 90 minutes</li> <li>(20 minutes dripping/50 minutes drying phase (35-40 °C)/20 minutes cooling phase)</li> <li>Low temperatures, poor ventilation and high humidity delay drying.</li> <li>Thinning</li> <li>Concentrate can be diluted up to a ratio of 1:3 with water.</li> </ul>                                                                                                       |  |  |
| Notes                                                                              | Observe the information sheets "Upkeep and Maintenance of Dipping Tanks and Flow Coating Facilities" and "Information on Workplace Hygiene".                                                                                                                                                                                                                                                                                                                 |  |  |
| Tools / Cleaning                                                                   | Brush, dipping tank, flow coating facility, spraying equipment                                                                                                                                                                                                                                                                                                                                                                                               |  |  |
|                                                                                    | Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use.<br>Ensure that any residue from cleaning is disposed of correctly.                                                                                                                                                                                                                                                                                                         |  |  |
| Storage / Shelf life                                                               | If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep<br>for at least 12 months.                                                                                                                                                                                                                                                                                                              |  |  |
| Safety data / Regulations                                                          | For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.                                                                                                                                                                                                                                                                         |  |  |
| Personal protective equipment                                                      | Respiratory protection with at least an A/P2 combination filter must be worn during spraying, together with safety goggles. Wear suitable protective gloves and clothing.                                                                                                                                                                                                                                                                                    |  |  |
| Disposal                                                                           | Larger quantities of leftover product should be disposed of in the original containers in accordance with the<br>applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with<br>household waste. Do not allow to enter the sewage system. Do not empty into drains.                                                                                                                                       |  |  |

Technical Data Sheet Product number 3786





EU limit value for the product (Cat. A/e): max. 130 g/l (2010). This product contains < 130 g/l VOC.

Induline SW-935

VOC content as per the "Decopaint" Directive (2004/42/EC)



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.