




Aqua MM-825 Matting Agent

Matting paste for water-based coating materials

Availability	
Quantity per pallet	288
Size / Quantity	
Container code	01
Art. no.	
3875	■

Range of use



- Matting paste for reducing the degree of gloss
- Not suitable for matt coating systems
- For use by professionals

Property profile



- Reduces the degree of gloss in water-based coating materials
- Variable reduction in degree of gloss possible

Characteristic data of the product

Density (20 °C)	Approx. 1.04 g/cm ³
Viscosity (20 °C)	Approx. 3700 mPas


The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products

- Aqua CL-440 Colour Opaque (3802)
- Aqua SL-418 Finish (5310)
- Aqua TL-412 Stair Varnish (2372)
- Aqua DL-65 Top PU (7200)
- Aqua DSL-55 High Build Stain PU (7220)
- Aqua MSL-45/sm Medium Build Stain UV+ (7130)
- Induline DW-610 (2482)
- Induline LW-710 (3987)
- Induline GW-310* (3385)
- Induline DW-601 Aqua Stop (1725)
- Induline LW-700 (3400)
- Induline LW-720 (3996)

*Use biocidal products carefully.
Always read the label and product information before use.

Production of the mixture



Mixing ratio	up to 4%
---------------------	----------

Using the Patent Disperser, work into the coating material while stirring.
Avoid mixing in dried product residues from opened containers.
The more matt the base material, the lower the matting effect.

Directions

- Conditions for use
See the Technical Data Sheet for the coating material used.

Seal opened containers well and use contents as soon as possible.

Tips on use

Check colour, adhesion and compatibility with the substrate by setting up a trial area.
Adding the product may affect the chemical and technical characteristics of the varnished surface.

Application examples


Gloss reduction achieved by adding 4% Aqua MM-825:



Products	Gloss reduction
Induline DW-601 Aqua Stop	Approx. 15 - 20 units
Induline LW-700	Approx. 10 - 15 units
Induline LW-720	Approx. 15 - 20 units
Aqua CL-440	Approx. 10 - 15 units
Aqua SL-418	Approx. 10 - 15 units
Aqua DSL-55	Approx. 10 - 15 units
Aqua DL-65	Approx. 15 - 20 units
Induline GW-310	Clear & base C: approx. 30 - 35 units; base A: approx. 10 - 15 units
Induline DW-610	Base A: approx. 10 - 15 units; base C: approx. 30 - 35 units
Induline LW-710	Approx. 30 units
Aqua MSL-45	Approx. 10 - 15 units

Notes Please contact Remmers Technical Service before adding to a product that is not listed.

Storage / Shelf life If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.



Safety data / Regulations For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.