



Tex 5/100 [eco]

Reinforcement fabric made from natural fibres

Availability	
Quantity per pallet	30
Size / Quantity	
Type of container	Roll
Container code	01
Art. no.	
4826	■

Application rate Approx. 1.1 m²/m²



Range of use



- Reinforcement inlay in MB 2K [eco]
- Absorption of movements of the substrate
- Crack repair

Property profile

- Based on renewable raw materials
- Permanently elastic
- Non-slip

Possible system products

- MB 2K [eco] (2940)

Directions

Stapling

Staple the fabric on the sanded, vacuumed wood planks after priming the substrate and allowing to dry. Staple approx. 6 times per m².
Overlapping zone ≥ 10 cm lengthwise and crosswise.

Adhesive bonding


Push the fabric into the coating mass over its entire area.
Overlapping zone ≥ 10 cm lengthwise and crosswise.

Notes

Deviations from applicable regulations must be agreed separately.
The relevant test certificates must be observed when planning and carrying out work.

Storage / Shelf life

Store upright in original container in a dry place.



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.