



Induline LW-722 [eco]

Resource-conserving, water-based, transparent intermediate and finishing coat for wood-aluminium building elements



Colour	Availability			
	Quantity per pallet	96	22	4
	Size / Quantity	5 l	20 l	120 l
	Type of container	Tin bucket	Tin bucket	Plastic drum
	Container code	05	20	68
	Art. no.			
Induline LW-722/10 [eco] dull matt				
clear	5100	■	■	■
special colours	5101	■	■	■

Application rate

Approx. 125-225 ml/m² (plus spraying losses)
(corresponds to a wet film thickness of 125-225 µm and dry film thickness of 40-80 µm)



Range of use



- Soft and hard woods
- Dimensionally stable wood/aluminium building elements: e.g. wood/aluminium windows and doors
- Protected constructions without direct outdoor exposure
- Intermediate and finishing coats
- Single coat and multi-coat procedure
- For use by professionals

Property profile



- This product is based on a balanced-biomass binding agent. 100% of the fossil raw materials have been replaced with renewable raw materials for the production of the binding agent.
- Good flow properties
- Block resistant (in accordance with Code of Practice HO.03)
- UV-resistant and colourfast
- Reduces grain emphasis and yellowing of wood substrate
- Pleasant feel

Characteristic data of the product

Viscosity (20 °C; 29 s-1)	Approx. 2600 mPas
Binder	Acrylate
Density (20 °C)	Approx. 1.03 g/cm ³
Odour	Characteristic
Degree of gloss	Dull matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- [French VOC Emission Test](#)

Possible system products

- [Induline SW-900* \(3776\)](#)
- [Induline SW-935 \(3786\)](#)
- [Induline GW-306* \(3488\)](#)
- [Induline GW-360 \(3201\)](#)
- [Induline GW-390 \(7950\)](#)
- [Induline ZW-502i \(1633\)](#)
- [Induline ZW-504i \(3453\)](#)



- Induline ZW-507i (1636)
- Induline Mix & Go (1827)

*Use biocidal products carefully.
Always read the label and product information before use.

Preparation

- Substrate requirements
The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.
Dimensionally stable wood building elements: wood moisture content 11-15%
- Substrate preparation
If necessary, impregnate non-resistant woods with a wood preservative* (*Use biocides safely. Always read the label and product information before use).
Pre-treat using a suitable primer & intermediate coat and carry out intermediate sanding if necessary.
If necessary, protect parapet joints with Induline V-Joint Protection or Induline AF-920.

Directions



- Conditions for use
Temperature of the object, environment and material: +15 °C to +30 °C.

The values given are based on undiluted material. The best spraying pattern is achieved if the material has a temperature of 15-20 °C.
Airless spraying: nozzle size: 0.28-0.33 mm; material pressure: 70-90 bar.
Air-mix spraying: nozzle size: 0.28-0.33 mm; material pressure: 70-90 bar, atomiser air pressure 1-2 bar.
Seal opened containers well and use contents as soon as possible.

Tips on use



- Check colour, adhesion and compatibility with the substrate by setting up a trial area.
Ensure good ventilation.
Do not use in direct sunlight or at temperatures below +15 °C or above +30 °C.
Substances in oak may bleed, causing dark discolouration, when coated with water dilutable dispersion stains.
To prevent any substances in the wood from becoming active, forced drying should be carried out.
The clear colour version of the product is not suited for use on exterior surfaces that are directly exposed to weather.
The system finder on our website www.remmers.com contains coating recommendations for specific wood types to be used when treating windows and exterior doors.
- Drying
Dust-dry: after approx. 1 hour
Ready for sanding and overcoating: after approx. 4 hours
Practice values at 23 °C and 50% relative humidity.
If forced drying is used, can be sanded and overcoated: after 20 minutes flash-off zone (at approx. 20 °C and 65 - 75% RH) / 75 minutes drying phase (approx. 45 °C, 1 m/s air circulation) / 20 minutes cooling phase
- Thinning
With water if required (max. 5%).

Notes

Sealing compounds must be compatible with the coating and may only be applied once the coating has dried thoroughly.
Only use sealing profiles that are free of plasticisers.
This product can be used with Induline Mix & Go to produce an easy-to-apply lacquer for reconditioning and repair work.
Wood is subjected to great climatic and environmental stresses when outdoors. The coat is susceptible to the processes of natural ageing, wear and decomposition. Decomposition takes place at different speeds, depending on the stress (weak, average, strong) placed on the wood building element. Weathering stages may vary according to the part or element affected. To give wood the longest and best possible protection it is advisable to examine surfaces every year. Any damage found should be addressed immediately after cleaning.
For cleaning and care, we recommend the care set for windows (2745)
We recommend that repairs be carried out using Aqua HSL-35/m Professional Wood Protection Stain 3in1* and Aqua DSL-55 High Build Stain PU. (*Use biocides safely. Always read the label and product information before use.)
Observe current standards and guidelines for coating wood building elements outdoors (Codes of Practice issued by the German Association of Window and Facade Manufacturers (VFF), Code of Practice No. 18 issued by the German Federal Committee for Paint and the Protection of Material Assets (BFS), guidelines issued by the German Lacquer and Printing Ink Association (VdL) and ift guidelines issued by the Institut für Fenstertechnik).

Tools / Cleaning




Hand spray gun, automatic spraying equipment
Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use.
Ensure that any residue from cleaning is disposed of correctly.



Storage / Shelf life

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Personal protective equipment

Respiratory protection with at least an A/P2 combination filter must be worn during spraying, together with safety goggles. Wear suitable protective gloves and clothing.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Biocidal Products Regulation

Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!

VOC content as per the
"Decopaint" Directive
(2004/42/EC)

EU limit value for the product (Cat. A/e): max. 130 g/l (2010).
This product contains < 130 g/l VOC.

VOC	
Kat.	A/e
2010:	130g/l
max.:	130g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.