Technical Data Sheet Product number 5430







HK Stain 3 in 1 [plus]

Fast-drying premium wood protection stain with reduced solvent content and enhanced moisture protection for exterior wood



Colour	Availability					
	Quantity per pallet	672	200	96	30	22
	Size / Quantity	3 x 0,75 l	2 x 2,5 l	2 x 5 l	10 I	201
	Type of container	Tin canister				
	Container code	01	03	05	10	20
	Art. no.					
light oak (RC-365)	5431					
clear	5432					
pine (RC-270)	5433					
nutwood (RC-660)	5434					
palisander (RC-720)	5435					
stone pine/larch (RC-760)	5436					
teak (RC-545)	5437					
rustic oak (RC-360)	5444					
mahogany (RC-565)	5446					
white (RC-990)	5451					
chestnut (RC-555)	5453					
ebony (RC-790)	5454					
fir green (RC-960)	5455					
special colours	5443					

Application rate

Approx. 100 ml/m² per coat, at least 2 coats required

$ \begin{array}{c c} 100 \text{ ml} \\ \downarrow & \downarrow & \downarrow \\ 1m^2 \end{array} $	Planed or very thick woods are less absorbent and may require a third coat
Range of use	 For use on exterior wood Wood without ground contact Wood building elements with no dimensional stability: e.g. fences, framework, carports, planking Wood building elements with limited dimensional stability, e.g. folding shutters, matchboarding, summerhouses Dimensionally stable wood building elements (when used as a primer only): e.g. windows and doors Primer, intermediate and finishing coats Not suitable for coating flooring (terraces, wooden decking, etc.)
Property profile	 3 in 1: impregnation, priming and stain Protects wood from moisture and UV radiation Impregnation effect: saturates wood to protect against moisture Diffusion-open protective film: moisture can escape Water-repellent: wet surfaces dry quickly Protection against weathering (constructive protection and the protection provided by the product) reduces the risk of blue stain and rot Film protects coating against blue stain, mould and algae Quick drying: 2 coats can be applied in one day Uniformly matte surfaces in brilliant colours Environmentally compatible: low solvent content



	 Long-term protection with Subsequent treatment with Low-build stain 	n uniform weathering and no flaking hout sanding			
Characteristic data of the product	Binder	Acrylate/alkyd system			
	Density (20 °C)	Approx. 1.03 g/cm ³			
	Pigmentation	Lightfast, highly transparent pigments			
	Odour	Mild, odourless once dry			
	Degree of gloss Matt				
	The values stated represent ty	pical characteristic data of the product and are not to be understood as binding product specifications			
Additional information	 Colour chart Sustainability data sheet 				
Preparation	manner. Dimensionally stable woo Wood building elements v Substrate preparation Completely remove old co Remove loose and torn kr thinner & brush cleaner). Smooth, planed wood sur absorption.	 The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner. Dimensionally stable wood building elements: wood moisture content 11-15% Wood building elements with limited or no dimensional stability: wood moisture content max. 18% Substrate preparation Completely remove old coatings (e.g. paints or medium-build stains), bark, bast and dirt. Remove loose and torn knots as well as resin that bleeds and clean with a suitable product (e.g. Remmers thinner & brush cleaner). Smooth, planed wood surfaces should be sanded and dusted before the coating is applied to ensure better 			
Directions	 Conditions for use Temperature of the material, air and substrate: from min. +8 °C to max. +25 °C. Stir well. Apply by brush. Apply in the direction of the grain. Apply a second coat once the first has dried. When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur. Seal opened containers well and use contents as soon as possible. 				
Tips on use	Before coating technically conduct a suitability test of If the surface is overcoate Clear, white and hemlock roof eaves, or as base coa Due to the different cover depending on the substra due to substances contain Due to the low UV protect In order to take account of surface meets expectation Rainfall may cause water cedar, afzelia, redwood, e Pre-testing is recommend In order to avoid the use of water-repellent (avoid ho splash water contact, sha required outdoors, the un safely. Always read the la Cut end-grain surfaces at End-grain and cut surface	ing properties of white and pastel varnish colours, the optical appearance may vary te. It must be checked in advance whether discolouration of the varnish may occur ned in the wood. tion of these colour shades, shorter maintenance intervals must be expected. f and clarify these issues, a trial surface must be prepared in order to ensure that the ns. soluble substances to bleed from wood that is rich in such substances, e.g. oak, red tc. This may lead to the discolouration of light-coloured masonry or render. led also on other woods. of wood preservatives as far as possible, the construction should be designed to be viziontal surfaces, open end-grain wood, capillary joints, water and moisture pockets, rp edges). If this cannot be guaranteed or if an even higher level of protection is treated wood can be impregnated with Wood Preservative Primer* (*Use biocides bel and product information before use). the bottom to create a water-drip edge. es should then be protected from moisture with end grain protection.			
	Cut end-grain surfaces at End-grain and cut surface	the bottom to create a water-drip edge. Is should then be protected from moisture with end grain protection. In a more intense colour and a glossier finish.			

1 100000000000
TT 3 M



Practice values at +20 °C and 65% relative humidity. Low temperatures, poor ventilation and high humidity delay drying.

	Thinning Ready to use				
Notes	On planed larch and softwoods with a high resin content, the coating may have reduced adhesion and resistance to weathering. This is especially the case on horizontal year rings, knots and areas of winter growth that are high in resin. Maintenance and renovation must be carried out more frequently on these surfaces. The only remedy for this is pre-weathering or very coarse sanding (P80). If these wood types are rough-sawn, considerably longer maintenance and renovation intervals are to be expected.				
Tools / Cleaning	Brush with synthetic bristles				
	Clean tools immediately after use with water and detergent. Ensure that any residue from cleaning is disposed of correctly.				
Storage / Shelf life	At least 36 months in unopened, original containers stored cool, dry and protected from frost.				
Safety data / Regulations	For further information on the safety aspects of transporting, storing and handling the product and on dispo and environmental matters, please see the current Safety Data Sheet.				
Disposal	Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together w household waste. Do not allow to enter the sewage system. Do not empty into drains.				
Biocidal Products Regulation	Contains as "treated goods" a biocidal product (film preservative) with the biocidal active agent 3-iodo-2- propynyl butylcarbamate to protect the film from contamination by microbial organisms (algae, mould etc.). Always follow the directions carefully!				
VOC content as per the "Decopaint" Directive (2004/42/EC)	EU limit value for the product (Cat. A/e): max. 130 g/l (2010). This product contains < 130 g/l VOC.				
VOC Kat. A/e 2010: 130g/ max.: 130g/					

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.