



Betofix EM SR 2K

PCC I (RM) concrete replacement mortar for static repair of concrete structures

Type/Name	Availability			
	Quantity per pallet	40	24	1
	Size / Quantity	25 kg	25 l	1000 l
	Type of container	Paper bag	Plastic canister	Container
	Container code	25	25	61
	Art. no.			
Betofix EM SR 2K	5786	■		
Betofix EM LQ SR	5787		■	■
Please note: Betofix EM LQ SR is the corresponding mixing liquid, please order separately under its own art. no.! Minimum purchase: 3 pallets, for silo goods 15 tonnes/silo.				

Application rate

Approx. 2.0 kg/m²/mm layer thickness or 2.0 kg/dm³



Range of use

- Concrete replacement for structurally relevant repairs
- Concrete substitution according to
 - DIN EN 1504-3
 - DIN 19573

Property profile

- High sulphate resistance
- High mechanical resistance
- High resistance to water penetration
- Very low shrinkage
- Can be applied by machine
- Freeze/thaw-resistant

Planning information

Betofix EM SR 2K - classification							
acc. to DIN EN 1504-3	R4						
Old concrete classes	A3	A4					
Reaction to fire	Class A2fl-s1 (DIN EN 13501-1)						
Impacts from the environment							
Carbonation	XC1	XC2	XC3	XC4			
Chlorides excluding seawater	XD1	XD2	XD3				
Chlorides from seawater	XS1	XS2	XS3				
Freeze/thaw attack with or without de-icing agent	XF1	XF2	XF3	XF4			
Chemical attack	XA1	XA2*	XA3**				
	* excluding sulfate attack						
	** protective measures required for						
	- chemical attack or higher						
	- high water flow rate and involvement of chemicals						
Moisture class assignment	W0	WF	WA				
Application							
Repair principles/procedures	3.1	3.2	4.4	5.3	6.3	7.1	7.2 7.4



Characteristic data of the product

Shrinkage	28 days: -0.51 mm/m
Bulk density	Approx. 1.8 kg/dm ³
Flexural strength	7 days: 8 N/mm ² 28 days: 12 N/mm ²
Compressive strength	7 days: 47 N/mm ² 28 days: 55 N/mm ²
Maximum grain size	4 mm
Bulk density of fresh mortar	Approx. 2.3 kg/dm ³
Consistency	Plastic

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products

- **Betofix EM LQ SR (5787)**
- **Betofix KHB EM SR (5788)**

Preparation

■ **Substrate requirements**

Concrete surface:

Stable, clean, dust-free

Observe the applicable technical regulations for the following parameters:

- Adhesive pull strength of the substrate
- Minimum roughness/roughness depth


Pre-wet the substrate so that it is slightly moist.

■ **Substrate preparation**

Reinforcement:

Degree of purity SA 2 ½ if applying corrosion protection, otherwise SA 2

Production of the mixture




■ **Mixing**

2.3 l Betofix EM LQ SR with 25 kg Betofix EM SR 2K

Prepare mixing liquid, add dry mortar and mix until homogeneous.

Mixing time: approx. 4 minutes

Directions



■ **Conditions for use**

Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.

Low temperatures increase, while high temperatures decrease the working and setting time.

Once it has hardened, mortar must not be made workable again by adding either water or more wet mortar.

Working time

(+20 °C): Approx. 60 minutes

Layer thickness

Single layer 12 mm to 50 mm

A bonding layer is required when applying manually.

Apply wet-on-wet.

Subsequent processing

Protect fresh mortar surfaces from wind, direct sunlight, rain and/or frost for at least 3 days so that they do not dry too quickly.

Machine working

Please contact Remmers Technical Service (phone +49 5432 83900) before applying with machine processing.

Tools / Cleaning



Mixing tool, trowel, aluminium rule, smoothing trowel, power trowel

Clean tools with water while the material is still fresh.


Remmers tools

- **Mischgefäß (4030)**
- **Profile Trowel (5047)**
- **Rundkelle (4114)**
- **Smoothing Trowel (4004)**
- **Smoothing Trowel Duo (4118)**
- **Schwammbrett gelb (4936)**
- **Latex float (4548)**



Storage / Shelf life

If stored in an unopened container and in a dry place, the product will keep for approx. 12 months.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Declaration of conformity



Remmers GmbH

Bernhard-Remmers-Str. 13, D – 49624 Lönningen

22

GBI-P 84-1

EN 1504-3: 2005

5786

Product for structural and non structural repair for concrete

Compressive strength:	class R4
Chloride ion content:	< 0.05 %
Adhesive bond:	≥ 2 MPa
Carbonation resistance:	passed
Elastic modulus:	≥ 20 GPa
Thermal compatibility part 1 & 4:	≥ 2 MPa
Capillary absorption:	≤ 0.5 kg/(m ² h ^{0.5})
Reaction to fire:	class A2fl-s1 (DIN EN 13501-1)

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.