



Epoxy BS 3000 M

Water-based, pigmented, matt sealant



| Colour | Availability | | | |
|----------------------------|---------------------|------------|------------|---|
| | Quantity per pallet | | | |
| Size / Quantity | 5 kg | 10 kg | 25 kg | |
| Type of container | Tin bucket | Tin bucket | Tin bucket | |
| Container code | 06 | 11 | 26 | |
| Art. no. | | | | |
| pebble grey | 6371 | ■ | ■ | ■ |
| silver grey | 6372 | ■ | ■ | ■ |
| light grey | 6373 | | ■ | ■ |
| special colours from 20 kg | 6370 | ■ | ■ | ■ |

Application rate See application examples

Range of use

- Sealant in Remmers Water Vapour Diffusion-Open systems
- Topcoat on Remmers Water Vapour Diffusion-Open blinded coatings
- Topcoat in the system Remmers Deck OS 8 WD-LE

Property profile



- Matt
- Low emissions
- Anti-slipping version possible
- Water vapour diffusion capable
- Contains no plasticisers, nonylphenols or alkylphenols
- Physiologically harmless once fully cured

Characteristic data of the product

■ On delivery

| | |
|----------------|-------------|
| Solids content | 68% by mass |
|----------------|-------------|

■ On delivery

| | Component A | Component B | Mixture |
|-------------------|-----------------------|-----------------------|-----------------------|
| Density (20 °C) | 1.4 g/cm ³ | 1.1 g/cm ³ | 1.4 g/cm ³ |
| Viscosity (25 °C) | 750 mPa s | 750 mPa s | 1400 mPa s |

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- Fire test (classification)
- Declaration of concordance
- TÜV PROFICERT-PRÉMIUM_Remmers WDD_Certificate
- TÜV PROFICERT-PRÉMIUM_Remmers WDD_Annex

Possible system products

- Epoxy BS 2000 (6001)
- Epoxy BS 4000 (6320)
- Add 250 (6271)

Preparation

■ Substrate requirements


The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.

The substrate must be prepared using suitable Remmers Water Vapour Diffusion-Open products.

For OS 8 systems, please see the corresponding test certificate.



Production of the mixture



- Combi-container
Add the entire quantity of the hardener (component B) to the base compound (component A).
Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).
Pour the mixture into a separate container and mix again thoroughly.
Mix for at least 3 minutes.
Insufficient mixing is indicated by streaks forming.

| | |
|-----------------------------|-----------------------|
| Mixing ratio (A : B) | 84:16 parts by weight |
|-----------------------------|-----------------------|

As soon as the mixture is ready to use, apply all of it to the prepared surface and spread it using a suitable tool.

Directions



For professional users only!

- Conditions for use
During the curing process, the applied material should be protected from moisture which could impair the surface and impair the adhesion.
Relative humidity should not exceed 80%.
The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.
Good ventilation must be ensured so that water can be released into the air.
If necessary, divide the surface into several small fields.
- Working time (+20 °C)
approx. 30 minutes
- Waiting time (+20 °C)
Waiting time between coats from min. 8 hours to max. 48 hours.
In the case of longer waiting times, sand the surface treated in the previous work step and apply primer again.
- Drying time (+20 °C)
Foot traffic after 1 day, mechanical loads after 3 days, full loading capacity after 7 days.

The times given are reduced at higher temperatures and increased at lower temperatures, in particular in combination with high humidity.

Application examples

- Sealant
Pour the material generously onto the surface. Use a suitable tool, e.g. a rubber scraper, to distribute the material, then roll using an epoxy roller.

| | |
|-------------------------|---|
| Application rate | approx. 0.15-0.25 kg/m ² binder per coat |
|-------------------------|---|

- Top sealant
Pour the material generously onto the surface. Use a suitable tool, e.g. a rubber scraper, to distribute the material, then roll using an epoxy roller.
Multiple layers must be applied. Dilute the resin mixture for the first application with 5% by mass of water.

| | |
|-------------------------|---|
| Application rate | approx. 0.60-0.80 kg/m ² binder per coat |
|-------------------------|---|

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C) using standard colours. Slight deviations from these values may arise if the product is worked with on site.

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.

When repairing surfaces or working up to existing surfaces, there will be a visible transition in appearance, texture and degree of gloss.

Shades of colour with low hiding power (e.g. yellow, red or orange) tend to have a translucent effect on the subsequently applied sealant. In such cases, a colour-coordinated construction, e.g. light grey, is necessary.

The sealant has a slightly textured surface typical for this type of system.

In order to achieve even surfaces, appropriate allowances for roughness depth must be taken into consideration. Abrasive mechanical loads leave traces of wear.

Suitable for vehicle traffic with rubber tyres; not suitable for vehicle loads with metal or polyamide tyres nor for dynamic point loads.

Epoxy resins are generally not colourfast when exposed to UV light or weather.

The colour stability of the sealant can be improved by using a UV-absorbent polyurethane sealant.

Observe the corresponding test certificate for OS 8 systems.

Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.



Tools / Cleaning

Toothed trowel, smoothing trowel, brush, epoxy roller and mixing apparatus




More detailed information can be found in the Remmers Tool Programme.
Clean tools, equipment and any splashed material immediately with water while still fresh.
Take suitable protective and waste disposal measures when cleaning.

Remmers tools

➤ [Patentdispenser \(4747\)](#)

Storage / Shelf life

If stored in unopened original containers in a cool, dry and frost-free place, the product will keep for min. 9 months (component A) or 24 months (component B).



Safety data / Regulations

For professional users only!

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet and the brochure entitled "Epoxy Resins in the Construction Industry and the Environment", issued by Deutsche Bauchemie e.V. (2nd edition 2009).

Personal protective equipment

This information can be obtained from the current Safety Data Sheets and/or the relevant professional associations.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

VOC content as per the
"Decopaint" Directive
(2004/42/EC)

EU limit value for the product (Cat. A/j): max. 140 g/l (2010).
This product contains < 140 g/l VOC.

Declaration of performance

➤ [Declaration of performance](#)

Declaration of conformity



Remmers GmbH

Bernhard-Remmers-Straße 13, D-49624 Lönningen

11

GBIII 047_4

EN 13813:2002

6370

Synthetic resin screed for use internally in buildings

| | |
|----------------------------------|----------------|
| Reaction to fire: | E _n |
| Release of corrosive substances: | SR |
| Wear resistance: | ≤ AR 1 |
| Bond strength: | ≥ B 1.5 |
| Impact resistance: | ≥ IR 4 |

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.