



Color LA Historic

- Historic Scumble -

Semi-scumbling, "true" silicone resin paint

Colour	Availability		
	Quantity per pallet	48	32
	Size / Quantity	5 l	12,5 l
	Type of container	Plastic bucket	Plastic bucket
	Container code	05	13
	Art. no.		
Special colours*	6476	■	■

* Only available upon consultation – intensive colours not possible

Application rate

Approx. 0.1 - 0.15 l/m² per coat

Application rates may vary depending on the condition of the surface.

Apply to a large enough trial area to determine the precise amount required.



Range of use

- Porous, mineral building materials
- Historically valuable and protected monuments
- Not suitable for working over plastic, thermoplastic and elastic coating systems.



Property profile

- Semi-scumbling
- Highly water vapour permeable $s_d \leq 0.1$ m
- Highly water-repelling $w \leq 0.1$ kg/(m² · h^{0.5})
- Reversible
- Low-stress
- Matt, mineral character
- Lime paint look



Characteristic data of the product

■ On delivery

Binder	Organosilicon modified copolymers
Density (20 °C)	Approx. 1.4 g/cm ³ depending on the colour
Viscosity	2000 mPa·s
Pigmentation	Inorganic, alkali resistant, absolutely light-fast oxide pigments, TiO ₂ -free
pH value	8 - 9

■ Once fully cured

Water vapour permeability (DIN 52615)	$s_d < 0.10$ m
Water absorption coefficient (DIN 52617)	$w < 0.1$ kg/(m ² · h ^{0.5})
Degree of gloss	Matt, mineral character

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products


- Antihygro (0616)
- Primer HF (6438)
- Primer Hydro HF (0725)
- Color LA Fill Historic (6471)
- Remmers Reinigungsprodukte
- KSE products



Preparation

- Substrate requirements
Dry, clean, free of dust and cracks and capable of supporting a load.
Free of salts known to be damaging to building materials.
- Substrate preparation
Use Primer HF or Primer Hydro HF to prime any sanding, firmly adhering substrates.
If necessary, strengthen or consolidate the substrate using silicic acid ester (KSE) products (see also guidelines for KSE modular system).

Directions



Stir well.
Coat the surface using a suitable tool.
Depending on the conditions of the substrate, apply 1 or 2 coats.
Wait at least 6 hours between coats.

Tips on use

Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product.
When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.
Protect freshly coated surfaces from rain, direct sunlight, frost and condensation.
When coating continuous surfaces, only use materials with the same batch number.

Notes

Deviations from applicable regulations must be agreed separately.
Always set up a trial area/trial areas first.

Tools / Cleaning



Brush, surface brush, lamb's wool roller
Clean tools, equipment and any splashed material immediately with water while still fresh.

- Remmers tools
- Flächenstreicher (4540)
 - Farbrolle FC (4913)
 - Rollerbügel (4449)
 - Epoxy Roller (5045)
 - Heizkörperpinsel (4541)

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/c) max. 40 g/l (2010).
This product contains < 40 g/l.

VOC	
Kat. 2010:	A/c 40g/l
max.:	40g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.