



ESD Blinding Material Fine (SIC 03)

Conductive hard material

Availability	
Quantity per pallet	40
Size / Quantity	25 kg
Type of container	Paper bag
Container code	25
Art. no.	
6683	■

Range of use ■ Blinding material in Remmers systems

Property profile

- Electrically conductive
- Dust-free
- Abrasion resistant
- Grain size: 0.25 - 0.45 mm

Characteristic data of the product

Grain density	3.2 g/cm ³
Form	Solid
Particle size	Approx. 0.25 - 0.45 mm

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Application examples

- Blinding material

Generously and evenly broadcast an excess of the material into a suitable Remmers coating while it is still wet. Remove any loose, excess material after hardening.


Application rate	approx. 4 - 6 kg/m ² incl. excess
------------------	--

Notes

Different grain sizes will always differ slightly in appearance, even if they are the same colour. Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

Storage / Shelf life

Unlimited if stored dry.



Safety data / Regulations

For professional users only!

Further information concerning safety during transport, storage and handling as well as on disposal and ecology can be found in the latest Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.