



QP Primer Cat

Accelerator for QP Primer

Availability	
Quantity per pallet	2000
Size / Quantity	0,05 kg
Type of container	Can
Container code	81
Art. no.	
6931	■

Application rate Dependent on application (see application examples)

Range of use ■ Accelerator for QP Primer

Property profile ■ Accelerates full hardening

Possible system products > [QP Primer \(6930\)](#)

Production of the mixture ■ **Mixing**
 Add the entire quantity of the hardener (component B) to the base compound (component A).
 Then add all of component C (QP Primer Cat) together with the accelerator (a second container of QP Primer Cat).
 Mix for at least 3 minutes.
 Insufficient mixing is indicated by streaks forming.

Directions For professional users only!

■ **Conditions for use**
 See the Technical Data Sheet for the binder being used.

■ **Working time (+20 °C)**
 With addition of 0.05 kg QP Primer Cat per container unit

approx. 18 min. at +20 °C
 approx. 40 min. at +10 °C
 approx. 100 min. at +5 °C

■ **Waiting time (+20 °C)**



With addition of 0.05 kg QP Primer Cat per container unit

approx. 45 min. at +20 °C
approx. 120 min. at +10 °C
approx. 400 min. at +5 °C

■ **Drying time (+20 °C)**

With addition of 0.05 kg QP Primer Cat per container unit

approx. 126 min. at +20 °C
approx. 340 min. at +10 °C
approx. 1100 min. at +5 °C


As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C) using standard colours. Slight deviations from these values may arise if the product is worked with on site.

Storage / Shelf life

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 6 months.



Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Declaration of conformity



Remmers GmbH

Bernhard-Remmers-Str. 13, D – 49624 Lönningen

UKCA Remmers (UK) Limited

Unit 4, Lloyds Court, Manor Royal Crawley, RH10 9QU

CE 20 / UKCA 21

GBIII 149

EN 13813:2002

6930

Synthetic resin screed for use internally in buildings

Reaction to fire:	E _{fl}
Release of corrosive substances:	SR
Wear resistance:	≤ AR 1
Bond strength:	≥ B 1.5
Impact resistance:	≥ IR 4



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.