



## Epoxy BS 2000 Fast

Fast-acting, water-based, pigmented primer

Colour	Availability		
	Quantity per pallet		
	<b>Size / Quantity</b>	<b>5 kg</b>	<b>10 kg</b>
	Type of container	Tin bucket	Tin bucket
	Container code	06	11
	<b>Art. no.</b>		
light grey	6934	■	■

**Application rate** See application examples

**Range of use**

- Fast-acting primer in Remmers WDD systems
- Bonding layer on old coatings

**Property profile**

- Excellent adhesion on many substrates
- Water vapour diffusion capable
- Contains no plasticisers, nonylphenols or alkylphenols
- Physiologically harmless once fully cured



### Characteristic data of the product

	Component A	Component B	Mixture
Density (20 °C)	1.36 g/cm <sup>3</sup>	1.09 g/cm <sup>3</sup>	1.25 g/cm <sup>3</sup>
Viscosity (25 °C)	2000 mPa s	900 mPa s	360 mPa s

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

**Possible system products**

- [Epoxy BS 4000 \(6320\)](#)
- [Epoxy BS 3000 SG \(6380\)](#)
- [Epoxy BS 3000 M \(6370\)](#)

**Preparation**

- **Substrate requirements**  
The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.  
The tensile strength of the surface of the substrate must be at least 1.5 N/mm<sup>2</sup> on average (smallest individual value of at least 1.0 N/mm<sup>2</sup>), and the compressive strength must be at least 25 N/mm<sup>2</sup>.  
Substrates must have reached their moisture balance and must also be protected against moisture penetration from the reverse side, including during use.



Concrete	max. 6 m% moisture
Cement screed	max. 6 m% moisture
Anhydrite screed	max. 0.3 m% moisture
Magnesite screed	2-4 m% moisture

In the case of anhydrite and magnesite screeds, moisture cannot be permitted to penetrate from building elements or the ground.

As a general principle, systems which permit the diffusion of water vapour are recommended for use with anhydrite and magnesite screeds.


The suitability of the coating on ceramic coverings, old coatings, levelling compounds and interior mastic asphalts (AS-IC 10) must be checked beforehand, if needed trial surfaces must be set up.

#### ■ Substrate preparation

Prepare the substrate by suitable means, e.g. steel shot blasting, so that it meets the specifications listed above.

Broken out or missing areas in the substrate should be filled flush with the surface using Remmers PCC systems or Remmers EP mortars.

#### Production of the mixture



#### ■ Combi-container

Stir component B homogeneously immediately before use.

Add the entire quantity of the hardener (component B) to the base compound (component A).

Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).

Pour the mixture into a separate container and mix again thoroughly.

Mix for at least 3 minutes.

Insufficient mixing is indicated by streaks forming.

On highly absorbent substrates the product can be diluted with water up to 10 % by mass.

Mixing ratio (A : B)	66.7 : 33.3 parts by weight
----------------------	-----------------------------

As soon as the mixture is ready to use, apply it in full to the prepared surface and spread it using suitable tools.

#### Directions



For professional users only!

#### ■ Conditions for use

Temperature of the material, air and substrate: from min. +12 °C to max. +30 °C.

During the curing process, the applied material should be protected from moisture which could impair the surface and impair the adhesion.

Relative humidity should not exceed 80%.

The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.

Good ventilation must be ensured so that water can be released into the air.

#### ■ Working time (+20 °C)

Max. 30 minutes

#### ■ Waiting time (+20 °C)



Waiting time between coats min. 2 hours and max. 6 hours.  
In the case of longer waiting times, sand the surface treated in the previous work step and apply primer again.

■ **Drying time (+20 °C)**

Foot traffic after 2-4 hours depending on the substrate, mechanical loads after 3 days, full loading capacity after 7 days.

The times given are reduced at higher temperatures and increased at lower temperatures, in particular in combination with high humidity.

**Application examples**

■ **Priming**

Apply the mixed resin generously to the surface. Distribute with a suitable tool, e.g. rubber blade, and work into the substrate with an epoxy roller so that pores in the surface of the substrate are completely filled.

It may be necessary to apply several layers.

Application rate	approx. 0.15 - 0.25 kg/m <sup>2</sup> binder (depending on the substrate)
------------------	---

**Notes**

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C) using standard colours. Slight deviations from these values may arise if the product is worked with on site.  
Primers must always be applied so that all pores are filled; it may therefore be necessary to increase the application rate or to apply a second coat.  
Wetting problems are possible on non-absorbent or slightly hydrophobic substrates. In this case, the priming must be repeated a second time.  
The end of the pot life cannot be recognised by increased viscosity or temperature, thus the max. working time must be strictly observed.  
Epoxy resins are generally not colourfast when exposed to UV light or weather.  
Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.

**Tools / Cleaning**


Paintbrush, rubber scraper, epoxy roller, mixing device



More detailed information can be found in the Remmers Tool Programme.  
Clean tools, equipment and any splashed material immediately with water while still fresh. Take suitable protective and waste disposal measures when cleaning.

**Storage / Shelf life**

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 9 months.



**Safety data / Regulations**

For professional users only!  
For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet and the brochure entitled "Epoxy Resins in the Construction Industry and the Environment", issued by Deutsche Bauchemie e.V. (2nd edition 2009).

**Disposal**



---

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

---

Declaration of  
conformity



---

**Remmers GmbH**

Bernhard-Remmers-Str. 13, D – 49624 Lönigen

**UKCA Remmers (UK) Limited**

Unit 4, Lloyds Court, Manor Royal Crawley, RH10 9QU

---

CE 20 / UKCA 21

GBIII 155

EN 13813:2002

6934

---

Synthetic resin screed for use internally in buildings

---

Reaction to fire:	E <sub>fl</sub>
Release of corrosive substances:	SR
Wear resistance:	≤ AR 1
Bond strength:	≥ B 1.5
Impact resistance:	≥ IR 4

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.