



Natural Worktop Finish [eco]

Durable, dirt-repelling finish for interior wood



Colour	Availability		
		Quantity per pallet	360
	Size / Quantity	3 x 0,375 l	3 x 0,75 l
	Type of container	Tin bucket	Tin bucket
	Container code	83	01
	Art. no.		
clear	7697	■	■
natural look	7698	■	■

Application rate


40 - 50 ml/m² per coat

The application rate depends heavily on the absorbency of the wood and the final sanded finish. 2 coats, apply thinly by brush or roller.

After every coat, remove excess material using a lint-free cotton cloth after approx. 20 - 30 min.



Range of use



- Interior wood
- Kitchen equipment made of wood
- Tables and worktops
- High-quality solid wood furniture
- "Natural look" colour only for light-coloured woods, such as oak, ash and spruce

Property profile

- Made from at least 90% renewable raw materials
- A vegan product based on the information available to us
- Easy to apply
- Penetrates deeply into the wood and emphasises the grain
- Long-lasting, dirt-repelling and hard-wearing
- Thin protective film against dirt and moisture
- Good resistance against selected standard household substances in accordance with DIN 68861, 1B (e. g. water, cola, beer, tea, coffee, wine & cleaning agents)
- Recyclable metal container

Characteristic data of the product

Binder	Alkyd resin based on renewable raw materials
Density (20 °C)	Approx. 0.96 g/cm ³
Viscosity	Approx. 500 mPas
Odour	Mild
Degree of gloss	Matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- **DIN EN 71-3 "Migration of certain elements"**
- **Safety declaration - food contact**

Test standards

Low emissions under the AgBB scheme

Additional information

- **Applying oil-based products with a cloth**
- **Maintenance of oiled surfaces**

Possible system products

- **MultiSil (7380)**
- **Care & Maintenance Kit (7739)**



Preparation

■ **Substrate requirements**

The substrate must be clean, dry, free of dust, grease and loose substances, and prepared in the correct manner.
Wood moisture content: 8-12%

■ **Substrate preparation**

Thoroughly remove any dirt, grease and non-adhering old coatings.
Wash off greasy and resin-rich wood with thinner and brush cleaner.
For furniture surfaces and similar objects, the sandpaper grit used for final sanding should be no finer than P180.

Directions



■ **Conditions for use**

Temperature of the material, air and substrate: from min. +15 °C to max. +30 °C.

Stir well.

Apply thinly using a surface brush or roller.

Smooth over to ensure that the product is distributed evenly on wood with different levels of absorbency.

Remove any excess material using a lint-free cotton cloth after approximately 20-30 minutes.

Use cotton rags/cloths on items of furniture.

After leaving to dry overnight, apply a second coat without sanding in between coats.

Inside cupboards and drawers, only apply a single thin layer of the product using a lint-free cotton cloth.

Tips on use



Check colour, adhesion and compatibility with the substrate by setting up a trial area.

Before coating technically modified woods and wood-based materials, apply the coating to a trial surface and conduct a suitability test on the desired area of use.

Only use on absorbent woods and substrates. Not suitable for surfaces that have already been varnished or sealed.

Ensure thorough ventilation during processing and drying.

Risk of spontaneous ignition (DGV Information 209-046). Do not use in the same workplace as NC-based varnishes or stains. Collect contaminated textiles (e.g. cleaning cloths, work clothing, dust bags) in fireproof waste containers and dispose of in a fireproof manner (under water).

■ **Drying**

Overcoating: after drying overnight

In the first few days: gentle use (e.g. limited exposure to water)

Recommended drying time before sealing with MultiSil: > 7 days (Remove smoothing agent residues immediately)

Practice values at +20 °C and 65% relative humidity.

Drying is dependent on the type of wood and the absorbency of the substrate.

Excess material on non-absorbent areas may delay drying, as will low temperatures, poor ventilation and high humidity.

■ **Thinning**

Ready to use

Notes

DIN EN 71-3 "Migration of certain elements":

This product complies with the limits for the migration of heavy metals to children's toys according to DIN EN 71-3 and thus fulfils one of several further requirements for the safety of children's toys according to the EU "Toy Directive" (2009/48/EC).

In the event of maintenance, treat the cleaned surface in such a way that it blends in to produce a uniform finish.

Remove water marks or stains on furniture with steel wool (grade 000) and apply a thin layer of the product.

Observe the "Care instructions for oiled surfaces and floors".

Tools / Cleaning



Brush with natural bristles, flat brush, velour roller, cotton rags/lint-free cotton cloth

Clean tools immediately after use with thinner and brush cleaner.

Ensure that any residue from cleaning is disposed of correctly.

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months.

Use the contents of open containers as quickly as possible.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal



Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Safety advice

Keep out of the reach of children.
 Use an A2/P2 combi-filter when spraying.
 Use a P2 dust filter when grinding or sanding.
 Ensure the area is thoroughly ventilated during application and drying.
 Do not eat, drink or smoke while using the paint.
 In the event of contact with the eyes or skin, rinse out thoroughly and immediately with water.
 Do not allow it to enter the ground, the sewage system or any bodies of water.
 Clean tools with soapy water immediately after use.
 Only send fully emptied containers for recycling.
 Take any leftover liquid material to the collection point for waste paint.

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (cat A/f): max. 700 g/l (2010).
 This product contains < 20 g/l VOC.

VOC	
Kat.	A/f
2010:	700g/l
max.:	20g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.