



# PU Concrete & Pavement Glaze

Polyurethane-reinforced exterior coating



Colour	Availability	
	Quantity per pallet	200
	<b>Size / Quantity</b>	<b>2,5 l</b>
	Type of container	Tin bucket
	Container code	03
	<b>Art. no.</b>	
anthracite	7778	■
red	7779	■
transparent	7780	■

### Application rate

Approx. 170 ml/m<sup>2</sup> per coat depending on the surface condition



### Range of use

- For absorbent, mineral or weathered substrates outdoors
- Not suitable for clinker paving stones and exposed aggregate concrete
- Use on private property



### Property profile

- High-quality refinishing coating for concrete slabs and paving stones
- Highly lightfast



### Characteristic data of the product

Density	1.05 g/cm <sup>3</sup>
Degree of gloss	Matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

### Additional information


➤ [Farbtonkarte](#)

### Preparation

- **Substrate requirements**  
The substrate must be dry, clean, capable of supporting a load, free from loose parts and residues of dust, release agent, oil and grease.
- **Substrate preparation**  
Use a high-pressure cleaner to thoroughly remove dirt, etc. from the existing substrate. Then clean by sweeping and allow the surface to dry.

### Directions

- **Conditions for use**  
Temperature of the material, air and substrate: from min. +10 °C to max. +30 °C.  
  
Stir well before using.  
Apply material evenly by brush or roller.  
Only apply in dry weather and at temperatures of 10 °C or above.  
Apply a second coat if necessary depending on the substrate.





**Tips on use**

Apply to a large enough trial area to determine the precise amount required.  
 Check the colour and the adhesion to the substrate by applying to a trial area.  
 Do not allow water to pool.  
 When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.  
 During processing and for at least 12 hours after application, do not allow any additional moisture to enter the reaction process.

■ **Drying**


Surface-dry: after approx. 2 hours  
 Overcoating: after approx. 12 hours  
 Full loading capacity: after approx. 24 hours  
 Practice values at +20 °C and 65% relative humidity.  
 Low temperatures and high humidity delay drying.

**Tools / Cleaning**



Paintbrush or lambskin paint roller  
 Clean tools, equipment and any splashed material immediately with water while still fresh.

**Storage / Shelf life**



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months.

**Safety data / Regulations**

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

**Disposal**

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

**Biocidal Products Regulation**

Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!

**VOC content as per the "Decopaint" Directive (2004/42/EC)**

EU limit value for the product (cat A/i): max. 140 g/l (2010).  
 This product contains < 140 g/l VOC.

VOC	
Kat.	A/i
2010:	140g/l
max.:	140g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.