



Acryl pro

- Acryl SK -

Plastoelastic sealing and adhesive compound

| Colour | Availability |
|-------------|-----------------------------|
| | Quantity per pallet 1056 |
| | Packaging unit 12 x 310 ml |
| | Type of container cartridge |
| | Container code 12 |
| | Art. no. |
| transparent | 7801 ■ |

Application rate Approx. 100 ml/m for a 1 cm² joint cross-section



Range of use



- Roofing trade
- Tinsmiths and installers
- General bonding work in construction and woodworking

Property profile



- High adhesive power even on damp substrates
- Compatible with bitumen
- Universal adhesion
- Can be overcoated
- Contains solvents

Characteristic data of the product

| ■ On delivery | |
|------------------------------|---------------------------------|
| Density (DIN EN ISO 1183-1A) | 1.07 g/cm ³ |
| Viscosity | Paste-like/stable |
| Skin formation | Approx. 15 min. (+23° C/50% RH) |

- Once fully cured



| | |
|--|------------------------|
| Elongation at break (DIN EN ISO 8339) | > 200% |
| E-modulus 100% (DIN EN ISO 8339) | 0.02 N/mm ² |
| Volume loss (DIN EN ISO 10563) | Approx. < 30% |
| Permissible total deformation (DIN EN 15651-1) | ± 7.5% |

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Possible system products > [Sealant Gun \(4701\)](#)

Preparation


■ **Substrate preparation**

The substrate must be clean, free of grease and capable of supporting a load. Metal must be bare.

Directions

■ **Conditions for use**

Temperature of the material, air and substrate: from min. -5 °C to max. +35 °C



Apply the material on one side, spread evenly and press the parts together. Use a moistened spatula to remove excess material.

Tips on use

When used on coatings, the material may cause (temporary) initial dissolving; set up a trial area.
Do not allow the product to come into contact with polystyrene.
Not for permanent water loads.
Do not heat the reacted material to above +60 °C.
Bubbles may form in the material when applied at high temperatures and in large gaps.

Notes

Deviations from applicable regulations must be agreed separately.
The relevant test certificates must be observed when planning and carrying out work.

Tools / Cleaning

Manual gun, sealant gun, spatula, joint smoothing trowel




Clean with V 101 in the fresh and reacted state.

Remmers tools

> [Sealant Gun \(4701\)](#)

Storage / Shelf life

At least 36 months in unopened, original containers stored cool, dry and protected from frost.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.



Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.