Technical Data Sheet Product number 7830







Induline LW-732 WF

Water-emulsified medium-build stain



Colour	Availability				
	Quantity per pallet	22	1	1	
	Size / Quantity	201	600 I	1000 I	
	Type of container	Tin bucket	Plastic container	Plastic container	
	Container code	20	63	61	
	Art. no.				
clear	7830				
special colours	7831				
pplication rate	80 - 120 ml/m² per coat				
80-120 ml					
↓ ↓ ↓ 1m ²					
lange of use	For use on interior and exterio	r wood			
	Soft and hard woods				
	 Building elements with no or limited dimensional stability For decorative design and for protecting laminated wood against dirt during transportation and construction 				
+ + L11	 For decorative design and for For use by professionals 	protecting laminat	ea wood against dirt during	transportation and construction	
roperty profile	Ready to use				
	 Quick drying 				
H ₂ 0	Easy to apply				
\approx	 Block resistant (in accordance with Code of Practice HO.03) Contains UV blockers to delay yellowing of the wood substrate 				
	Contains UV blockers to delay	venowing of the v	vood substrate		
	 Contains UV blockers to delay Free from film preservation an 				
	-				
	Free from film preservation an	d wood protection	biocides		
	 Free from film preservation an Binder 	d wood protection Acrylate	biocides		
	 Free from film preservation an Binder Density (20 °C) 	d wood protection Acrylate Approx. 1.03	biocides		
	 Free from film preservation an Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour 	d wood protection Acrylate Approx. 1.03 Approx. 24	biocides		
Characteristic data of the product	 Free from film preservation an Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt	biocides	derstood as binding product specificati	
product	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt	biocides	derstood as binding product specificati	
product	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of Induline SW-900* (3776) 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt	biocides	derstood as binding product specificati	
product	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt	biocides	derstood as binding product specificat	
product	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of Induline SW-900* (3776) Induline SW-900 IT* (3781) Induline SW-910 (3777) Aqua MSL-45/sm Medium But 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt characteristic data of	g/cm ³ the product and are not to be units (6)	derstood as binding product specificati	
product	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of Induline SW-900* (3776) Induline SW-900 IT* (3781) Induline SW-910 (3777) Aqua MSL-45/sm Medium But Aqua EAL-47/sm-Aqua Trans 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt characteristic data of	g/cm ³ the product and are not to be units (6)	derstood as binding product specificati	
	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of Induline SW-900* (3776) Induline SW-900 IT* (3781) Induline SW-910 (3777) Aqua MSL-45/sm Medium But 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt characteristic data of ild Stain UV+ (713 lucent Finishing C	g/cm ³ the product and are not to be une coat (3040)	derstood as binding product specificati	
product	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical Induline SW-900* (3776) Induline SW-900 IT* (3781) Induline SW-910 (3777) Aqua MSL-45/sm Medium But Aqua EAL-47/sm-Aqua Trans *Use biocidal products carefully. 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt characteristic data of ild Stain UV+ (713 lucent Finishing C	g/cm ³ the product and are not to be une coat (3040)	derstood as binding product specificati	
Possible system products	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical of Induline SW-900* (3776) Induline SW-900 IT* (3781) Induline SW-910 (3777) Aqua MSL-45/sm Medium But Aqua EAL-47/sm-Aqua Trans *Use biocidal products carefully. Always read the label and product in 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt characteristic data of ild Stain UV+ (713 lucent Finishing C	g/cm ³ the product and are not to be une coat (3040)		
roduct ossible system products	 Free from film preservation and Binder Density (20 °C) Runout time s (20° C, DIN 4) Odour Degree of gloss The values stated represent typical Induline SW-900* (3776) Induline SW-900 IT* (3781) Induline SW-910 (3777) Aqua MSL-45/sm Medium But Aqua EAL-47/sm-Aqua Trans *Use biocidal products carefully. Always read the label and product in 	d wood protection Acrylate Approx. 1.03 Approx. 24 Mild Silk matt characteristic data of ild Stain UV+ (713 lucent Finishing C formation before use.	g/cm ³ the product and are not to be und the product and are not to be und coat (3040) rease and loose substances	s, and prepared in the correct	

Induline LW-732 WF





	If necessary, impregnate non-resistant woods with a wood preservative* (*Use biocides safely. Always read the label and product information before use).			
Directions	Conditions for use Temperature of the material, air and substrate: from min. +5 °C to max. +25 °C.			
	Stir well, including during application or after a break in work. Apply with a brush, roller or by spraying.			
	Once dry, apply further coatings. Seal opened containers well and use contents as soon as possible.			
Tips on use	If you wish to use this product in a pigmented version (special colour), please consult Remmers Technical Service beforehand. Check colour, adhesion and compatibility with the substrate by setting up a trial area. Substances in oak may bleed, causing dark discolouration, when coated with water dilutable dispersion stains. If you wish to use this product outside its primary area of application (house and hall construction), please consult Remmers Technical Service beforehand.			
	Drying Can be overcoated: after approx. 2 hours (Practice values at 20 °C and 65% relative humidity)			
	Forced drying: after approx. 10 minutes flash-off zone (at approx. 20 °C and 65-70% RH) / 30 minutes drying phase (approx. 45 °C, 1 m/s air circulation) / 20 minutes cooling phase Low temperatures and high humidity delay drying.			
	Thinning Ready to use. If necessary with water (max. 5%)			
Notes	On planed larch and softwoods with a high resin content, the coating may have reduced adhesion and resistance to weathering. This is especially the case on horizontal year rings, knots and areas of winter growt that are high in resin. Maintenance and renovation must be carried out more frequently on these surfaces. Th only remedy for this is pre-weathering or very coarse sanding (P80). If these wood types are rough-sawn, considerably longer maintenance and renovation intervals are to be expected.			
Tools / Cleaning	Brush with synthetic bristles, flat brush, short-pile roller, airless/airmix spraying equipment, sponge, carpet board, mop Clean tools with water or Aqua RK-898 Cleaning Concentrate immediately after use. Ensure that any residue from cleaning is disposed of correctly.			
Storage / Shelf life	If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.			
Safety data / Regulations	For further information on the safety aspects of transporting, storing and handling the product and on disp and environmental matters, please see the current Safety Data Sheet.			
Personal protective equipment	Respiratory protection with a particle filter P2 must be worn during spraying, together with protective goggle Wear suitable protective gloves and clothing.			
Disposal	Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together we household waste. Do not allow to enter the sewage system. Do not empty into drains.			
Biocidal Products Regulation	Contains a biocidal product (in-can preservative) with the biocidal agents CMIT/MIT (3:1) for protecting the container content from deterioration by microbial organisms (germs, yeast, etc.). Please note the processing guidelines carefully!			
VOC content as per the "Decopaint" Directive (2004/42/EC)	EU limit value for the product (Cat. A/e): max. 130 g/l (2010). This product contains < 130 g/l VOC.			
VOC Kat. A/e 2010: 133g/l max.: 130g/l				

Technical Data Sheet







Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.